



BUILDING CODE COMPLIANCE OFFICE
METRO-DADE FLAGLER BUILDING
140 WEST FLAGLER STREET, SUITE 1603
MIAMI, FLORIDA 33130-1563
(305) 375-2901 FAX (305) 375-2908

CONTRACTOR LICENSING SECTION
(305) 375-2527 FAX (305) 375-2558

CONTRACTOR ENFORCEMENT DIVISION
(305) 375-2966 FAX (305) 375-2908

PRODUCT CONTROL DIVISION
(305) 375-2902 FAX (305) 372-6339

PRODUCT CONTROL NOTICE OF ACCEPTANCE

Carlisle SynTec Incorporated
P. O. Box 7000
Carlisle ,PA 17013

Your application for Notice of Acceptance (NOA) of:

Single-Ply Roofing Membrane-Gypsum Deck

under Chapter 8 of the Code of Miami-Dade County governing the use of Alternate Materials and Types of Construction, and completely described herein, has been recommended for acceptance by the Miami-Dade County Building Code Compliance Office (BCCO) under the conditions specified herein.

This NOA shall not be valid after the expiration date stated below. BCCO reserves the right to secure this product or material at any time from a jobsite or manufacturer's plant for quality control testing. If this product or material fails to perform in the approved manner, BCCO may revoke, modify, or suspend the use of such product or material immediately. BCCO reserves the right to revoke this approval, if it is determined by BCCO that this product or material fails to meet the requirements of the South Florida Building Code.

The expense of such testing will be incurred by the manufacturer.

Raul Rodriguez
Chief Product Control Division

ACCEPTANCE NO.: 00-0725.11
EXPIRES: 08/31/2003

**THIS IS THE COVERSHEET, SEE ADDITIONAL PAGES FOR SPECIFIC AND GENERAL
CONDITIONS
BUILDING CODE & PRODUCT REVIEW COMMITTEE**

This application for Product Approval has been reviewed by the BCCO and approved by the Building Code and Product Review Committee to be used in Miami-Dade County, Florida under the conditions set forth above.

Francisco J. Quintana, R.A.
Director
Miami-Dade County
Building Code Compliance Office

APPROVED: 08/31/2000

ROOFING SYSTEM APPROVAL

<u>Category:</u>	Roofing	Approval Date: August 31, 2000
<u>Sub-Category:</u>	Single Ply	Expiration Date: August 31, 2003
<u>Material:</u>	TPO	
<u>Deck Type:</u>	Poured Gypsum	
<u>Maximum Design Pressure</u>	-45 psf	
<u>Fire Classification:</u>	See General Limitation #1	

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

<u>Product Name</u>	<u>Dimensions</u>	<u>Test Specifications</u>	<u>Product Description</u>
Sure-Weld	various	PA 131	Reinforced white or colored TPO membrane.
Sure-Weld GSD	various	PA 131	Reinforced white or colored FR TPO membrane.
Carlisle Foamular Durapink Insulation	various	PA 110	Extruded Polystyrene for white or black mechanically fastened roof systems.
Carlisle Foamular 1/2" Board	various	PA 110	Extruded Polystyrene recovery board.
Carlisle Foamular 150, 250, 400, 404, 600	various	PA 110	Extruded Polystyrene insulation
Polyisocyanurate HP-H	various	PA 110	Polyisocyanurate roof insulation.
Polyisocyanurate HP-W	various	PA 110	Polyisocyanurate roof insulation.
Polyisocyanurate HP	various	PA 110	Polyisocyanurate roof insulation.
Polyisocyanurate HP-N	various	PA 110	Polyisocyanurate roof insulation.
Sure Seal EPS Insulation	various	PA 110	Expanded Polystyrene.
Sure-Weld Bonding Adhesive	various	PA 110	Solvent-based bonding adhesive.
Sure-Seal Insulation Plates	2 7/8" dia.	PA 114	Metal plates used for insulation securement.
Sure-Seal EPS/Fiberboard	various	PA 110	High Density Wood Fiberboard bonded to EPS.
Sure-Seal HP Recovery Board	various	PA 110	High Density Wood Fiberboard.
Sure-Seal HP Concrete Spikes	1/4" dia.	PA 114	Driven fasteners used for insulation and membrane securement in concrete decks.
Sure-Seal Lightweight Insulation Plates	3" dia.	PA 114	Metal plates used for insulation securement with HP Lightweight Fasteners.
Sure-Seal HP Lightweight Fasteners	0.687 dia.	PA 114	Threaded plastic fasteners for insulation and membrane securement in lightweight deck materials.


 Frank Zuloaga, RRC
 Roofing Product Control Examiner

<u>Product Name</u>	<u>Dimensions</u>	<u>Test Specifications</u>	<u>Product Description</u>
Piranha Seam Plates	2-3/8" dia.	PA 114	Metal plates used for membrane securement with Sure-Seal fasteners.
Sure-Seal Lightweight Seam Plates	2" dia.	PA 114	Metal plates used for membrane securement with HP Lightweight Fasteners.
Sure-Seal HP Fasteners	#14	PA 114	Threaded fasteners used for insulation securement in steel, wood and concrete decks.
Sure-Seal HP-X Fasteners	#15	PA 114	Threaded fasteners used for insulation and membrane securement in steel, wood and concrete decks.

TRADE NAMES OF PRODUCTS MANUFACTURED BY OTHERS:


<u>Product Name</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>	<u>Manufacturer</u>
Hy Therm	various	PA 110	Polyisocyanurate foam insulation	Apache Products Co.
Pyrox	various	PA 110	Polyisocyanurate foam insulation	Apache Products Co.
White Line	various	PA 110	Polyisocyanurate foam insulation	Apache Products Co.
ACFoam II	various	PA 110	Polyisocyanurate foam insulation	Atlas Energy Products
Hy-Therm Stable R	various	PA 110	Polyisocyanurate foam insulation	Celotex Corp.
Star AP	various	PA 110	Polyisocyanurate foam insulation	Celotex Corp.
Star SP	various	PA 110	Polyisocyanurate foam insulation	Celotex Corp.
Tristar	various	PA 110	Polyisocyanurate foam insulation	Celotex Corp.
Dekfast Fasteners #12		PA 114	Insulation fastener for steel and wood decks.	Construction Fasteners Inc.
Dekfast Fasteners #14		PA 114	Insulation fastener for steel and concrete decks.	Construction Fasteners Inc.
Dekfast Fasteners #15		PA 114	Insulation fastener for steel and concrete.	Construction Fasteners, Inc.
Dekfast Hex Plate	2 7/8" x 3 1/4"	PA 114	Galvalume hex stress plate.	Construction Fasteners Inc.
Styrofoam	2' x 8'	PA 110	Extruded polystyrene insulation	Dow


 Frank Zuloaga, RRC
 Roofing Product Control Examiner

<u>Product Name</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>	<u>Manufacturer</u>
ISO 95+ GL, 95+ GW		PA 110	Polyisocyanurate foam insulation	Firestone
Asphalt Primer		ASTM D 41	Asphalt Primer	generic
High Density Wood Fiberboard	various	PA 110	Wood fiber insulation board	generic
Oriented Strand Board	various	PA 110	Oriented strand insulation board.	generic
Perlite/Urethane Composite	various	PA 110	Perlite/urethane composite insulation board	generic
Sturdi-Top	various	PA 110	Wood fiber insulation board.	Georgia Pacific
Ultra/M-II	various	PA 110	Polyisocyanurate foam insulation	Homasote Co.
Insta-Stick	various	PA 110	Polyisocyanurate foam insulation	Insta-Foam
#12 Roofgrip		PA 114	Insulation fastener	ITW Buildex
#14 Roofgrip		PA 114	Insulation fastener	ITW Buildex
E'NERG'Y PSI-25	various	PA 110	Polyisocyanurate foam insulation	NRG Barriers, Inc.
E'NERG'Y-2	various	PA 110	Polyisocyanurate foam insulation	NRG Barriers, Inc.
CD-10 Fastener		PA 114	Insulation fastener	Olympic Manufacturing Group, Inc.
Con-Tite		PA 114	Concrete deck insulation fastener	Olympic Manufacturing Group, Inc.
Lite-Deck Fastener		PA 114	Insulation fastener	Olympic Manufacturing Group, Inc.
N.T.B. Magnum		PA 114	Glass reinforced nylon fastener for use in gypsum and cementitious wood fiber decks.	Olympic Manufacturing Group, Inc.
Olympic Fastener #14		PA 114	Insulation fastener	Olympic Manufacturing Group, Inc.
Olympic Fastener #12		PA 114	Insulation fastener	Olympic Manufacturing Group, Inc.
Multi-Max FA	various	PA 110	Polyisocyanurate foam insulation	RMAX
HD Insul-Fixx Fastener		PA 114	Insulation fastener for use in steel and concrete decks	SFS/Stadler


 Frank Zuloaga, RRC
 Roofing Product Control Examiner

<u>Product Name</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>	<u>Manufacturer</u>
Insul-Fixx Fastener		PA 114	Insulation fastener for steel and wood decks	SFS/Stadler
Insul-Fixx S	3" square	PA 114	3" square Galvalume AZ55 stress plate	SFS/Stadler
Insul-Fixx P	3" round	PA 114	3" round polyethylene stress plate	SFS/Stadler
Isofast Plate	various	PA 114	Square or oblong Galvalume steel plates for use with Isofast fasteners	SFS/Stadler
Isofast Fasteners		PA 114	Insulation fastener for steel and wood decks	SFS/Stadler
Rawl Fasteners #14		PA 114	Insulation fastener for use in steel, wood or concrete	The Rawlplug Company Inc.
Rawl Drive		PA 114	Insulation fastener and steel and plastic stress plate for concrete deck	The Rawlplug Company Inc.
Rawl Fasteners #12		PA 114	Insulation fastener for steel and wood decks	The Rawlplug Company Inc.
Rawl Spike		PA 114	Insulation fastener and steel and plastic stress plate for concrete deck	The Rawlplug Company Inc.
Rawl Speed-Lock Toggle Bolt		PA 114	Insulation fastener assembly	The Rawlplug Company Inc.
Rawlite		PA 114	Insulation fastener for cementitious and gypsum decks	The Rawlplug Company Inc.
Tru-Fast CF Fasteners		PA 114	Insulation fastener for concrete decks	Tru-Fast
Tru-Fast Ultra		PA 114	Stainless Steel fastener for use in steel, wood and concrete decks	Tru-Fast
Tru-Fast Plastic Plate	3.04" round	PA 114	3.04" round polyethylene plastic plate	Tru-Fast
Tru-Fast DL		PA 114	Glass reinforced nylon fastener for use in tectum or gypsum decks	Tru-Fast
Tru-Fast TP		PA 114	Insulation fastener for use in steel or wood decks	Tru-Fast
Tru-Fast HD		PA 114	Insulation fastener for use in wood, steel or concrete decks	Tru-Fast
Tru-Fast MP-3	3.23" round	PA 114	3.23" round Galvalume AZ50 steel plate	Tru-Fast
Tru-Fast DP		PA 114	Insulation fastener for use in steel or wood decks	Tru-Fast




Frank Zuloaga, RRC
Roofing Product Control Examiner

<u>Product Name</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>	<u>Manufacturer</u>
Insulcel		PA 110	Cellular insulating concrete system	W.R. Grace
Structodeck	various	PA 110	High Density Wood Fiber insulation board.	Wood Fiber Industries

EVIDENCE SUBMITTED:

<u>Test Agency</u>	<u>Test Identifier</u>	<u>Description</u>	<u>Date</u>
Architectural Testing Inc.	ATI-37490.01	Membrane Brittleness Testing	7/7/00
Factory Mutual Research Corporation	3Z9A1.AM	Wind Uplift and Fire Classification	10/15/97
Factory Mutual Research Corporation	Approval Guide Excerpt	Wind Uplift and Fire Classifications Listings	5/00
Celotex Corporation Testing Services	520257	Membrane Physical Property Testing	4/19/00
SGS U.S. Testing Company Incorporated	131248-R2	Membrane Ozone Resistance Testing	1/6/00



Frank Zuloaga, RRC
Roofing Product Control Examiner

SYSTEMS:

- Membrane Type:** Single Ply, Thermoplastic, TPO, Reinforced
- Deck Type 6I:** Poured Gypsum, Insulated, New Construction
- Deck Description:** Poured Gypsum Concrete
- System Type C:** All layers of insulation simultaneously fastened; membrane fully adhered.

All General and System Limitations apply.

<u>Insulation</u> <u>Base Layer</u>	<u>Fastener</u> <u>Type</u>	<u>Fastening</u> <u>Detail No.</u>	<u>Fasteners</u> <u>Per Board</u>	<u>Fastener</u> <u>Density</u>
--	--------------------------------	---------------------------------------	--------------------------------------	-----------------------------------

One of the following covered with the boards listed in Top Layer

Approved Type(s): Extruded Polystyrene				
Minimum: 1" x 4' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): Energy-Lok, AC Foam - II				
Minimum: 1" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): Perlite				
Minimum: 3/4" x 2' x 4'	N/A	N/A	N/A	N/A

<u>Insulation</u> <u>Base or Top Layer</u>	<u>Fastener</u> <u>Type</u>	<u>Fastening</u> <u>Detail No.</u>	<u>Fasteners</u> <u>Per Board</u>	<u>Fastener</u> <u>Density</u>
---	--------------------------------	---------------------------------------	--------------------------------------	-----------------------------------

One or more layers of the following:

Approved Type(s): AC Foam II				
Minimum: 1.5" x 3' x 4'	Rawlite	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Carlisle HP Lightweight	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	GTL	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Lite-Deck	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	NTB Magnum	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Iron-Lok	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Strap Toggle	[2]	6	1:2 ft. ²
Approved Type(s): E'NRG'Y-2, PSI-25				
Minimum: 1.4" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²


 Frank Zuloaga, RRC
 Roofing Product Control Examiner

<u>Insulation Base or Top Layer</u>	<u>Fastener Type</u>	<u>Fastening Detail No.</u>	<u>Fasteners Per Board</u>	<u>Fastener Density</u>
Approved Type(s): HP Recovery				
Minimum: ½" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²
Approved Type(s): High Density Fiberboard				
Minimum: ¾" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: ¾" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: ¾" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: ¾" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: ¾" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: ¾" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: ¾" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²
Approved Type(s): WHITELINE, PYROX, AP				
Minimum: 1.4" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²
Approved Type(s): AC Foam Composite, Rhoflex Composite, Fesco Foam				
Minimum: 1.5" x 3' x 4'	Rawlite	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Carlisle HP Lightweight	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	GTL	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Lite-Deck	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	NTB Magnum	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Iron-Lok	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Strap Toggle	[2]	6	1:2 ft. ²
Approved Type(s): Polyisocyanurate HP-W				
Minimum: 1.5" x 3' x 4'	Rawlite	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Carlisle HP Lightweight	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	GTL	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Lite-Deck	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	NTB Magnum	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Iron-Lok	[2]	6	1:2 ft. ²
Minimum: 1.5" x 3' x 4'	Strap Toggle	[2]	6	1:2 ft. ²



<u>Insulation Base or Top Layer</u>	<u>Fastener Type</u>	<u>Fastening Detail No.</u>	<u>Fasteners Per Board</u>	<u>Fastener Density</u>
Approved Type(s): Polyisocyanurate HP -W				
Minimum: 2" x 3' x 4'	Rawlite	[2]	6	1:2 ft. ²
Minimum: 2" x 3' x 4'	Carlisle HP Lightweight	[2]	6	1:2 ft. ²
Minimum: 2" x 3' x 4'	GTL	[2]	6	1:2 ft. ²
Minimum: 2" x 3' x 4'	Lite-Deck	[2]	6	1:2 ft. ²
Minimum: 2" x 3' x 4'	NTB Magnum	[2]	6	1:2 ft. ²
Minimum: 2" x 3' x 4'	Iron-Lok	[2]	6	1:2 ft. ²
Minimum: 2" x 3' x 4'	Strap Toggle	[2]	6	1:2 ft. ²
Approved Type(s): Polyisocyanurate HP				
Minimum: 1.4" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: 1.4" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²
Approved Type(s): Sturdi Top				
Minimum: ½" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²
Approved Type(s): Ultra/M-II Iso/glas				
Minimum: 1.2" x 3' x 4'	Rawlite	[2]	6	1:2 ft. ²
Minimum: 1.2" x 3' x 4'	Carlisle HP Lightweight	[2]	6	1:2 ft. ²
Minimum: 1.2" x 3' x 4'	GTL	[2]	6	1:2 ft. ²
Minimum: 1.2" x 3' x 4'	Lite-Deck	[2]	6	1:2 ft. ²
Minimum: 1.2" x 3' x 4'	NTB Magnum	[2]	6	1:2 ft. ²
Minimum: 1.2" x 3' x 4'	Iron-Lok	[2]	6	1:2 ft. ²
Minimum: 1.2" x 3' x 4'	Strap Toggle	[2]	6	1:2 ft. ²
Approved Type(s): Wood Fiber				
Minimum: 1" x 2' x 4'	Rawlite	[1]	4	1:2 ft. ²
Minimum: 1" x 2' x 4'	Carlisle HP Lightweight	[1]	4	1:2 ft. ²
Minimum: 1" x 2' x 4'	GTL	[1]	4	1:2 ft. ²
Minimum: 1" x 2' x 4'	Lite-Deck	[1]	4	1:2 ft. ²
Minimum: 1" x 2' x 4'	NTB Magnum	[1]	4	1:2 ft. ²
Minimum: 1" x 2' x 4'	Iron-Lok	[1]	4	1:2 ft. ²
Minimum: 1" x 2' x 4'	Strap Toggle	[1]	4	1:2 ft. ²



<u>Insulation Base or Top Layer</u>	<u>Fastener Type</u>	<u>Fastening Detail No.</u>	<u>Fasteners Per Board</u>	<u>Fastener Density</u>
Approved Type(s): Fiber Base				
Minimum: ½" x 4' x 8'	Rawlite	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Carlisle HP Lightweight	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	GTL	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Lite-Deck	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	NTB Magnum	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Iron-Lok	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Strap Toggle	[4]	16	1:2 ft. ²

<u>Insulation Top Layer</u>	<u>Fastener Type</u>	<u>Fastening Detail No.</u>	<u>Fasteners Per Board</u>	<u>Fastener Density</u>
-----------------------------	----------------------	-----------------------------	----------------------------	-------------------------

Required over the insulations listed in Base Layer or optional over any of the insulations listed as Base or Top Layer :

Approved Type(s): HP Recovery (for use over all insul. types)				
Minimum: ½" x 4' x 4'	Rawlite	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Carlisle HP Lightweight	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	GTL	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Lite-Deck	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	NTB Magnum	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Iron-Lok	[3]	8	1:2 ft. ²
Minimum: ½" x 4' x 4'	Strap Toggle	[3]	8	1:2 ft. ²

Approved Type(s): Fiber Base (for use over polyisocyanurate, gypsum or perlite)				
Minimum: ½" x 4' x 8'	Rawlite	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Carlisle HP Lightweight	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	GTL	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Lite-Deck	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Iron-Lok	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	NTB Magnum	[4]	16	1:2 ft. ²
Minimum: ½" x 4' x 8'	Strap Toggle	[4]	16	1:2 ft. ²

Note: Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners per board shall be increased maintaining the same fastener density (See Miami-Dade County Roofing Application Standard RAS 117 for fastener details).

Vapor Retarder: (Optional) Any UL or FMRC approved vapor retarder applied to the roof deck or over a base layer of insulation.

Barrier: None.

Membrane: Sure-Weld or Sure-Weld GSD, Reinforced, 45 or 60 mil membrane fully adhered to the insulation using Sure-Weld Bonding Adhesive applied to the substrate at a rate of 1 gal/60 ft.².

Maximum Design Pressure -45 psf (See General Limitation #9)


Maximum Fire Classification: See General Limitation #1.



Frank Zuloaga, RRC
Roofing Product Control Examiner

GENERAL LIMITATIONS

- 1 Fire classification is not part of this acceptance, refer to a current Approved Roofing Materials Directory for fire ratings of this product.
- 2 Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
- 3 All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
- 4 An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each sidelap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq. **Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**
- 5 Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
- 6 Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer or Architect may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Miami-Dade County Protocol TAS 105 and calculations in compliance with Miami-Dade Roofing Application Standard RAS 117.
- 7 Perimeter and corner areas shall comply with the enhanced uplift pressure of these areas, as calculated in compliance with Chapter 23 of the South Florida Building Code. Fastener densities shall be increase for both insulation and base sheet as calculated in compliance with Miami-Dade County Roofing Application Standard RAS 117. **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
- 8 All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform with Miami-Dade County Roofing Application Standard RAS 111 and the wind load requirements of Chapter 23 of the South Florida Building Code.
- 9 The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**



Frank Zuloaga, RRC
Roofing Product Control Examiner

NOTICE OF ACCEPTANCE STANDARD CONDITIONS

- 1 Renewal of this Acceptance (approval) shall be considered after a renewal application has been filed and the original submitted documentation, including test supporting data, engineering documents, are no older than eight (8) years.
- 2 Any and all approved products shall be permanently labeled with the manufacturer's name, city, state, and the following statement: "Miami-Dade County Product Control Approved", or as specifically stated in the specific conditions of this Acceptance.
- 3 Renewals of Acceptance will not be considered if:
 - a) There has been a change in the South Florida Building Code affecting the evaluation of this product and the product is not in compliance with the code changes;
 - b) The product is no longer the same product (identical) as the one originally approved;
 - c) If the Acceptance holder has not complied with all the requirements of this acceptance, including the correct installation of the product;
 - d) The engineer who originally prepared, signed and sealed the required documentation initially submitted, is no longer practicing the engineering profession.
- 4 Any revision or change in the materials, use, and/or manufacture of the product or process shall automatically be cause for termination of this Acceptance, unless prior written approval has been requested (through the filing of a revision application with appropriate fee) and granted by this office.
- 5 Any of the following shall also be grounds for removal of this Acceptance:
 - a) Unsatisfactory performance of this product or process;
 - b) Misuse of this Acceptance as an endorsement of any product, for sales, advertising or any other purposes.
- 6 The Notice of Acceptance number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the Notice of Acceptance is displayed, then it shall be done in its entirety.
- 7 A copy of this Acceptance as well as approved drawings and other documents, where it applies, shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at all times. The copies need not be resealed by the engineer.
- 8 Failure to comply with any section of this Acceptance shall be cause for termination and removal of Acceptance.
- 9 This Acceptance contains pages 1 through 12.

END OF THIS ACCEPTANCE

Frank Zuloaga, RRC
Roofing Product Control Examiner