MIAMI-DADE

MIAMI-DADE COUNTY, FLORIDA
METRO-DADE FLAGLER BUILDING

BUILDING CODE COMPLIANCE OFFICE
METRO-DADE FLAGLER BUILDING
140 WEST FLAGLER STREET, SUITE 1603
MIAMI, FLORIDA 33130-1563
(305) 375-2901 FAX (305) 375-2908

CONTRACTOR LICENSING SECTION
(305) 375-2527 FAX (305) 375-2558

CONTRACTOR ENFORCEMENT DIVISION
(305) 375-2966 FAX (305) 375-2908

PRODUCT CONTROL DIVISION
(305) 375-2902 FAX (305) 372-6339

PRODUCT CONTROL NOTICE OF ACCEPTANCE

Koppers Industries, Inc.
436 Seventh Avenue
Pittsburg ,OH 15219-1800

Your application for Notice of Acceptance (NOA) of:
Koppers Built-Up Roofing Products over Gypsum Decks
under Chapter 8 of the Code of Miami-Dade County governing the use of Alternate Materials and Types of Construction, and completely described herein, has been recommended for acceptance by the Miami-Dade County Building Code Compliance Office (BCCO) under the conditions specified herein.

This NOA shall not be valid after the expiration date stated below. BCCO reserves the right to secure this product or material at any time from a jobsite or manufacturer's plant for quality control testing. If this product or material fails to perform in the approved manner, BCCO may revoke, modify, or suspend the use of such product or material immediately. BCCO reserves the right to revoke this approval, if it is determined by BCCO that this product or material fails to meet the requirements of the South Florida Building Code.

The expense of such testing will be incurred by the manufacturer.

ACCEPTANCE NO.: 00-1108.04
EXPIRES: 12/30/2005

Raul Rodriguez
Chief Product Control Division

THIS IS THE COVERSHEET, SEE ADDITIONAL PAGES FOR SPECIFIC AND GENERAL CONDITIONS
BUILDING CODE & PRODUCT REVIEW COMMITTEE

This application for Product Approval has been reviewed by the BCCO and approved by the Building Code and Product Review Committee to be used in Miami-Dade County, Florida under the conditions set forth above.

Francisco J. Quintana, R.A.
Director
Miami-Dade County
Building Code Compliance Office

APPROVED: 12/28/2000

ROOFING SYSTEM APPROVAL

Category:	Roofing	**Approval Date: December 28, 2000**
Sub-Category:	Built-Up Roofing, Coal Tar	**Expiration Date: December 30, 2005**
Material:	Fiberglass, Polyester/Organic	
Deck Type:	Gypsum	
Maximum Design Pressure	-45 psf	
Fire Classification:	See General Limitation #1	

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

Product	Dimensions	Test Specification	Product Description
Coal Tar Bitumen	Available in 20 or 55 gallon drums or in bulk.	ASTM D 450 type III	Coal tar pitch used as a waterproof and adhesive material in conjuction with organic or inorganic felts.
Coal Tar Pitch	Available in 20 or 55 gallon drums or in bulk.	ASTM D 450 type I	Coal tar pitch used as a waterproof and adhesive material in conjuction with organic or inorganic felts.
Glass Fiber Base Sheet	Roll size: 36" x 108'	ASTM D-4601	Non-perforated, type II asphalt impregnated and coated glass fiber base sheet for use in conventional and modified bitumen built-up roofing.
Kop-R (WC)	various	PA 110	Polyisocyanurate and perlite composite insulation board.
Kop-R (WI)	various	PA 110	Polyisocyanurate foam insulation.
Kop-R (WII)	various	PA 110	Polyisocyanurate foam insulation board.
Kop-R High Density Wood Fiber	various	PA 110	Wood fiber insulation board.
Koppers Polyester Roofing Felt	8 sq./roll	Proprietary	Spunbond polyester plysheet for use in conventional built-up roofing.
No. 15 Tarred Felt Ply Sheet	Roll size: 36" x 144'	ASTM D 227	Organic fiber based felt saturated with refined coal tar.
Organic Base Sheet	Roll size: 36" x 75'	ASTM D 2626	Non-perforated, organic fiber based felt saturated and coated with asphalt surfaced with a parting agent.

Frank Zuloaga, RRC
Roofing Product Control Examiner

Product	Dimensions	Test Specification	Product Description
Tar-Glas Ply Sheet	Roll Size: 36"x 108'	ASTM D 4990	A coal tar impregnated and coated glass fiber ply sheet for use in conventional built-up roofing.
Tar-Glas Premium Ply Sheet	Roll size: 36" x 108'	ASTM D 4990	A coal tar imperegnated and coated glass fiber ply sheet for use in conventional bitumen built-up roofing.

TRADE NAMES OF PRODUCTS MANUFACTURED BY OTHERS:

Product	Dimensions	Test Specification	Product Description	Manufacturer
ACFoam II	various	PA 110	Polyisocyanurate foam insulation	Atlas (with current NOA)
E'NRG'Y-2, PSI-25	various	PA 110	Polyisocyanurate foam insulation	Johns Manville (with current NOA)
HyTherm AP	various	PA 110	Polyisocyanurate foam insulation	Celotex (with current NOA)
Pyrox	various	PA 110	Polyisocyanurate foam insulation	Apache (with current NOA)
E'NRG'Y-2 Plus	various	PA 110	Polyisocyanurate composite insulation	Johns Manville (with current NOA)
ACFoam Composite	Various	PA 110	Polyisocyanurate composite insulation	Atlas (with current NOA)
Fiberglass	various	PA 110	Fiberglass roof insulation	See Approved Systems Listings
Perlite Insulation	various	PA 110	Perlite insulation board	See Approved Systems Listings
High Density Wood Fiberboard	various	PA 110	Wood fiber insulation board	See Approved Systems Listings
Nail Tite Type 'A' or Type 'R'	Various	PA 114	Base sheet fastener for gypsum decks	ES Products (with current NOA)
Olympic CR Base Ply Fastener	Various	PA 114	Base sheet fastener for lightweight decks	Olympic (with current NOA)
NTB Magnum	Various	PA 114	Insulation fastener for lightweight decks	Olympic (with current NOA)
LiteDeck	Various	PA 114	Insulation fastener for lightweight decks	Olympic (with current NOA)
Polymer Gyptec	Various	PA 114	Insulation fastener for lightweight decks	ITW Buildex (with current NOA)
Rawlite Fastener	Various	PA 114	Insulation fastener for lightweight decks	Rawlplug (with current NOA)
Tru-Fast TL	Various	PA 114	Insulation fastener for lightweight decks.	Tru-Fast (with current NOA)
Asphalt Primer		ASTM D 41	Asphalt Primer	generic

Frank Zuloaga, RRC
Roofing Product Control Examiner

Product	Dimensions	Test Specification	Product Description	Manufacturer
Coal Tar Priming Oil		ASTM D 43	Coal tar based primer	generic

EVIDENCE SUBMITTED:

Test Agency	Name	Report	Date
Factory Mutual Research Corporation	J.I. 1W5A1.AM	I-90 Wind Classification	08/12/93
Factory Mutual Research Corporation	FM Approval Guide	Insulation attachment requirements	Published Annually
Underwriters Laboratories, Inc.	UL Roofing Materials and Systems Directory	Fire Classifications	Published Annually
Dynatech Engineering	1.94.17	Wind Uplift, Small Scale	01/17/94
Dynatech Engineering	4301-12.94-1	Wind Uplift	12/05/94
Dynatech Engineering	4301-12.94-2	Wind Uplift	12/05/94
Dynatech Engineering	4302-1.95-2	Wind Uplift	01/03/95
Dynatech Engineering	4302-1.95-4	Wind Uplift	01/04/95
Exterior Research & Design, LLC.	4302.02.97-1	PA 114(D)	02/15/97

Frank Zuloaga, RRC
Roofing Product Control Examiner

APPROVED ASSEMBLIES:

Deck Type 6I: Poured Gypsum, Insulated, New Construction

Deck Description: Poured gypsum concrete

System Type A: Anchor sheet mechanically attached, all layers of insulation adhered with approved asphalt or coal tar pitch

All General and System Limitations apply.

Insulation Base Layer	Fastener Type	Fastening Detail No.	Fasteners Per Board	Fastener Density
One or more layers of the following:				
Approved Type(s): **Kop-R(WII), AC-Foam II, Pyrox, HyTherm AP**				
Minimum: 1.0" x 4' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **E'NRG'Y 2, PSI-25**				
Minimum: 1.0" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **E'NRG'Y 2 Plus, Kop-R Composite, Kop-R(WC), ACFoam Composite**				
Minimum: 1.5" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Standard or Wide Flute Armor-R Glass, Fiberglas Roof Insulation or Fiber Glass Roof Insulation**				
Minimum: 15/16" x 4' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Kop-R Wood Fiber, Armor Board Regular or High Density Fiberboard, Esgard Fiberboard, Celotex Regular or High Density Fiberboard, Traffic Top, High Density Roof Fiberboard, GAFTEMP Regular or High Density Fiberboard, Huebert Fiberboard**				
Minimum: ½" x 2' x 4'	N/A	N/A	N/A	N/A

Insulation Top Layer	Fastener Type	Fastening Detail No.	Fasteners Per Board	Fastener Density
One or more layers of the following:				
Approved Type(s): **E'NRG'Y 2 Plus, Kop-R Composite, Kop-R(WC), ACFoam Composite**				
Minimum: 1.5" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Standard or Wide Flute Armor-R Glass, Fiberglas Roof Insulation or Fiber Glass Roof Insulation**				
Minimum: 15/16" x 4' x 4'	N/A	N/A	N/A	N/A

Frank Zuloaga, RRC
Roofing Product Control Examiner

Approved Type(s): **Kop-R Wood Fiber, Armor Board Regular or High Density Fiberboard, Esgard Fiberboard, Celotex Regular or High Density Fiberboard, Traffic Top, High Density Roof Fiberboard, GAFTEMP Regular or High Density Fiberboard, Huebert Fiberboard**

Minimum: ½" x 2' x 4'	N/A	N/A	N/A	N/A

Approved Type(s): **Celotherm, ConPerl, GAFTEMP Permalite, Fesco Board**

Minimum: ¾" x 2' x 4'	N/A	N/A	N/A	N/A

Note: All insulation shall be adhered to the anchor sheet in full mopping of approved hot asphalt within the EVT range and at a rate of 20-40 lbs/100 ft^2. Please refer to Roofing Application Standard RAS 117 for insulation attachment. Insulation listed as base layer only shall be used only as base layers with a second layer of approved top layer insulation installed as the final membrane substrate. Composite insulation panels may be used as a top layer placed with the polyisocyanurate side facing down.

Anchor Sheet:	Koppers Glass Fiber or Organic base sheet attached as note below.
Fastening #1:	ES Products Nail-Tite Type 'A' or Type 'R', FM-90 or FM-60 fasteners or Olympic CR Base Felt Fasteners + CR Base Sheet Discs spaced 9" o.c. at the lap and two rows staggered 18" o.c. in the field.
	or
Fastening #2:	ES Products Nail-Tite Type 'A' or Type 'R', FM-90 or FM-60 fasteners or Olympic CR Base Felt Fasteners + CR Base Sheet Discs spaced 7½" o.c. at the lap and 7½" o.c. in one row in the center of the sheet.
Base Sheet:	(Optional) Koppers organic or glass fiber base sheet adhered to the insulation substrate with approved asphalt at an application rate of 25 lbs./sq. ± 15%.
Ply Sheet:	Two or more plies of Koppers Tarred Felt, Glass Felt, Tar-Glas, Premium Tar-Glas or Polyester Roofing Felt. Roof cover may be Glass Fiber Felt, Tar-Glas or Premium Tar-Glas Felt adhered in a full mopping of approved coal tar at an application rate of 25 lbs./sq. ± 15%.
Cap Sheet:	None.
Surfacing:	Flood coat of coal tar with an application rate of 70 lbs./sq.; plus gravel or slag at application rates of 400 and 300 lbs./sq., respectively.
Maximum Design Pressure:	-45 psf
Maximum Fire Classification:	See General Limitation #1.
Maximum Slope:	See General Limitation #1.

Frank Zuloaga, RRC
Roofing Product Control Examiner

Deck Type 6I: Gypsum, Insulated, New Construction

Deck Description: Poured Gypsum

System Type B: Base layer of insulation mechanically fastened, top layer adhered with approved bitumen

All General and System Limitations shall apply.

Insulation Base Layer	Fastener Type	Fastening Detail No.	Fasteners Per Board	Fastener Density
One or more layers of the following:				
Approved Type(s): **AC-Foam II**				
Minimum: 1.5" x 4' x 4'	TruFast TL	[3]	4	1:4 ft²
Approved Type(s): **E'NRG'Y 2, PSI-25**				
Minimum: 1.5" x 3' x 4'	Polymer Gyptec	[2]	4	1:3 ft²
Minimum: 1.5" x 3' x 4'	Olympic NTB Mag.	[2]	4	1:3 ft²
	Olympic LiteDeck	[2]	4	1:3 ft²
Minimum: 1.5" x 3' x 4'	Rawlite	[2]	4	1:3 ft²
Minimum: 1.5" x 3' x 4'	TruFast TL	[2]	4	1:3 ft²
Minimum: 2.0" x 3' x 4'	Polymer Gyptec	[2]	3	1:4 ft²
Minimum: 2.0" x 3' x 4'	Olympic NTB Mag.	[2]	3	1:4 ft²
	Olympic LiteDeck	[2]	3	1:4 ft²
Minimum: 2.0" x 3' x 4'	Rawlite	[2]	3	1:4 ft²
Minimum: 2.0" x 3' x 4'	TruFast TL	[2]	3	1:4 ft²
Approved Type(s): **E'NRG'Y 2 Plus, Kop-R Composite, Kop-R(WC), ACFoam Composite**				
Minimum: 1.5" x 3' x 4'	Polymer Gyptec	[2]	3	1:4 ft²
Minimum: 1.5" x 3' x 4'	Olympic NTB Mag.	[2]	3	1:4 ft²
	Olympic LiteDeck	[2]	3	1:4 ft²
Minimum: 1.5" x 3' x 4'	Rawlite	[2]	3	1:4 ft²
Minimum: 1.5" x 3' x 4'	TruFast TL	[2]	3	1:4 ft²
Approved Type(s): **Standard or Wide Flute Armor-R Glass, Fiberglas Roof Insulation or Fiber Glass Roof Insulation**				
Minimum: 15/16" x 4' x 4'	Polymer Gyptec	[3]	6	1:2.67 ft²
Minimum: 15/16" x 4' x 4'	Olympic NTB Mag.	[3]	6	1:2.67 ft²
	Olympic LiteDeck	[3]	6	1:2.67 ft²
Minimum: 15/16" x 4' x 4'	Rawlite	[3]	6	1:2.67 ft²
Minimum: 15/16" x 4' x 4'	TruFast TL	[3]	6	1:2.67 ft²

Frank Zuloaga, RRC
Roofing Product Control Examiner

Approved Type(s): **Kop-R Wood Fiber, Armor Board Regular or High Density Fiberboard, Esgard Fiberboard, Celotex Regular or High Density Fiberboard, Traffic Top, High Density Roof Fiberboard, GAFTEMP Regular or High Density Fiberboard, Huebert Fiberboard**

Minimum: 1.0" x 2' x 4'	Polymer Gyptec	[1]	4	1:2 ft²
Minimum: 1.0" x 2' x 4'	Olympic NTB Mag.	[1]	4	1:2 ft²
	Olympic LiteDeck	[1]	4	1:2 ft²
Minimum: 1.0" x 2' x 4'	Rawlite	[1]	2	1:4 ft²
Minimum: 1.0" x 2' x 4'	TruFast TL	[1]	2	1:4 ft²

Approved Type(s): **Celotherm, ConPerl, GAFTEMP Permalite, Fesco Board**

Minimum: ¾" x 2' x 4'	Polymer Gyptec	[1]	4	1:2 ft²
Minimum: ¾" x 2' x 4'	Olympic NTB Mag.	[1]	4	1:2 ft²
	Olympic LiteDeck	[1]	4	1:2 ft²
Minimum: ¾" x 2' x 4'	Rawlite	[1]	4	1:2 ft²
Minimum: ¾" x 2' x 4'	TruFast TL	[1]	4	1:2 ft²

Note: Base layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).

Insulation Top Layer	Fastener Type	Fastening Detail No.	Fasteners Per Board	Fastener Density
One or more layers of the following:				
Approved Type(s): **E'NRG'Y 2 Plus, Kop-R Composite, Kop-R(WC), ACFoam Composite**				
Minimum: 1.5" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Standard or Wide Flute Armor-R Glass, Fiberglas Roof Insulation or Fiber Glass Roof Insulation**				
Minimum: 15/16" x 4' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Kop-R Wood Fiber, Armor Board Regular or High Density Fiberboard, Esgard Fiberboard, Celotex Regular or High Density Fiberboard, Traffic Top, High Density Roof Fiberboard, GAFTEMP Regular or High Density Fiberboard, Huebert Fiberboard**				
Minimum: ½" x 2' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Celotherm, ConPerl, GAFTEMP Permalite, Fesco Board**				
Minimum: ¾" x 2' x 4'	N/A	N/A	N/A	N/A

Note: Apply top layer of insulation in a full mopping of any approved mopping hot asphalt within the EVT range and at a rate of 20-40 lbs/100 ft^2. Please refer to Roofing Application Standard RAS 117 for insulation attachment. Insulation listed as Base Layer only shall be used only as base layers with a second layer of approved top layer insulation installed as the final membrane substrate. Composite insulation panels may be used as a top layer placed with the polyisocyanurate side facing down.

Frank Zuloaga, RRC
Roofing Product Control Examiner

Base Sheet:	(Optional) Koppers organic or glass fiber base sheet adhered to the insulation substrate with approved asphalt at an application rate of 25 lbs./sq. ± 15%.
Ply Sheet:	Two or more plies of Koppers Tarred Felt, Glass Felt, Tar-Glas, Premium Tar-Glas or Polyester Roofing Felt . Roof cover may be Glass Fiber Felt, Tar-Glas or Premium Tar-Glas Felt adhered in a full mopping of approved coal tar at an application rate of 25 lbs./sq. ± 15%.
Cap Sheet:	None.
Surfacing:	Flood coat of coal tar with an application rate of 70 lbs./sq.; plus gravel or slag at application rates of 400 and 300 lbs./sq., respectively.
Maximum Design Pressure:	-45 psf
Maximum Fire Classification:	See General Limitation #1.
Maximum Slope:	See General Limitation #1.

Frank Zuloaga, RRC
Roofing Product Control Examiner

Deck Type 5I: Gypsum, Insulated, New Construction

Deck Description: Poured Gypsum

System Type C: All layers of insulation simultaneously attached.

All General and System Limitations shall apply.

Insulation Base Layer	Fastener Type	Fastening Detail No.	Fasteners Per Board	Fastener Density
One or more layers of the following:				
Approved Type(s): **Kop-R(WII), AC-Foam II, Pyrox, HyTherm AP**				
Minimum: 1.0" x 4' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **E'NRG'Y 2, PSI-25**				
Minimum: 1.0" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **E'NRG'Y 2 Plus, Kop-R Composite, Kop-R(WC), ACFoam Composite**				
Minimum: 1.5" x 3' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Standard or Wide Flute Armor-R Glass, Fiberglas Roof Insulation or Fiber Glass Roof Insulation**				
Minimum: 15/16" x 4' x 4'	N/A	N/A	N/A	N/A
Approved Type(s): **Kop-R Wood Fiber, Armor Board Regular or High Density Fiberboard, Esgard Fiberboard, Celotex Regular or High Density Fiberboard, Traffic Top, High Density Roof Fiberboard, GAFTEMP Regular or High Density Fiberboard, Huebert Fiberboard**				
Minimum: ½" x 2' x 4'	N/A	N/A	N/A	N/A

Note: All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

Insulation Top Layer	Fastener Type	Fastening Detail No.	Fasteners Per Board	Fastener Density
One or more layers of the following:				
Approved Type(s): **E'NRG'Y 2 Plus, Kop-R Composite, Kop-R(WC), ACFoam Composite**				
Minimum: 1.5" x 3' x 4'	Polymer Gyptec	[2]	3	1:4 ft²
Minimum: 1.5" x 3' x 4'	Olympic NTB Mag.	[2]	3	1:4 ft²
	Olympic LiteDeck	[2]	3	1:4 ft²
Minimum: 1.5" x 3' x 4'	Rawlite	[2]	3	1:4 ft²
Minimum: 1.5" x 3' x 4'	TruFast TL	[2]	3	1:4 ft²

Frank Zuloaga, RRC
Roofing Product Control Examiner

Approved Type(s): **Standard or Wide Flute Armor-R Glass, Fiberglas Roof Insulation or Fiber Glass Roof Insulation**

Minimum: 15/16" x 4' x 4'	Polymer Gyptec	[3]	6	1:2.67 ft²
Minimum: 15/16" x 4' x 4'	Olympic NTB Mag.	[3]	6	1:2.67 ft²
	Olympic LiteDeck	[3]	6	1:2.67 ft²
Minimum: 15/16" x 4' x 4'	Rawlite	[3]	6	1:2.67 ft²
Minimum: 15/16" x 4' x 4'	TruFast TL	[3]	6	1:2.67 ft²

Approved Type(s): **Kop-R Wood Fiber, Armor Board Regular or High Density Fiberboard, Esgard Fiberboard, Celotex Regular or High Density Fiberboard, Traffic Top, High Density Roof Fiberboard, GAFTEMP Regular or High Density Fiberboard, Huebert Fiberboard**

Minimum: 1.0" x 2' x 4'	Polymer Gyptec	[1]	4	1:2 ft²
Minimum: 1.0" x 2' x 4'	Olympic NTB Mag.	[1]	4	1:2 ft²
	Olympic LiteDeck	[1]	4	1:2 ft²
Minimum: 1.0" x 2' x 4'	Rawlite	[1]	2	1:4 ft²
Minimum: 1.0" x 2' x 4'	TruFast TL	[1]	2	1:4 ft²

Approved Type(s): **Celotherm, ConPerl, GAFTEMP Permalite, Fesco Board**

Minimum: ¾" x 2' x 4'	Polymer Gyptec	[1]	4	1:2 ft²
Minimum: ¾" x 2' x 4'	Olympic NTB Mag.	[1]	4	1:2 ft²
	Olympic LiteDeck	[1]	4	1:2 ft²
Minimum: ¾" x 2' x 4'	Rawlite	[1]	4	1:2 ft²
Minimum: ¾" x 2' x 4'	TruFast TL	[1]	4	1:2 ft²

Base Sheet: (Optional) Koppers organic or glass fiber base sheet adhered to the insulation substrate with approved asphalt at an application rate of 25 lbs./sq. ± 15%.

Ply Sheet: Two or more plies of Koppers Tarred Felt, Glass Felt, Tar-Glas, Premium Tar-Glas or Polyester Roofing Felt ply sheet. Roofing cover may be Glass Fiber Felt, Tar-Glas or Premium Tar-Glas Felt adhered in a full mopping of approved coal tar at an application rate of 25 lbs./sq. ± 15%.

Cap Sheet: None.

Surfacing: Flood coat of coal tar with an application rate of 70 lbs./sq.; plus gravel or slag at application rates of 400 and 300 lbs./sq., respectively.

Maximum Design Pressure: -45 psf

Maximum Fire Classification: See General Limitation #1.

Maximum Slope: See General Limitation #1.

Frank Zuloaga, RRC
Roofing Product Control Examiner

GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance, refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each sidelap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq. **Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**
5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117. **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform with Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**

Frank Zuloaga, RRC
Roofing Product Control Examiner

NOTICE OF ACCEPTANCE STANDARD CONDITIONS

1 Renewal of this Acceptance (approval) shall be considered after a renewal application has been filed and the original submitted documentation, including test supporting data, engineering documents, are no older than eight (8) years.

2 Any and all approved products shall be permanently labeled with the manufacturer's name, city, state, and the following statement: "Miami-Dade County Product Control Approved", or as specifically stated in the specific conditions of this Acceptance.

3 Renewals of Acceptance will not be considered if:
a) There has been a change in the South Florida Building Code affecting the evaluation of this product and the product is not in compliance with the code changes;
b) The product is no longer the same product (identical) as the one originally approved;
c) If the Acceptance holder has not complied with all the requirements of this acceptance, including the correct installation of the product;
d) The engineer who originally prepared, signed and sealed the required documentation initially submitted, is no longer practicing the engineering profession.

4 Any revision or change in the materials, use, and/or manufacture of the product or process shall automatically be cause for termination of this Acceptance, unless prior written approval has been requested (through the filing of a revision application with appropriate fee) and granted by this office.

5 Any of the following shall also be grounds for removal of this Acceptance:
a) Unsatisfactory performance of this product or process;
b) Misuse of this Acceptance as an endorsement of any product, for sales, advertising or any other purposes.

6 The Notice of Acceptance number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the Notice of Acceptance is displayed, then it shall be done in its entirety.

7 A copy of this Acceptance as well as approved drawings and other documents, where it applies, shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at all times. The copies need not be resealed by the engineer.

8 Failure to comply with any section of this Acceptance shall be cause for termination and removal of Acceptance.

9 This Acceptance contains pages 1 through 13.

END OF THIS ACCEPTANCE

Frank Zuloaga, RRC
Roofing Product Control Examiner