



**BUILDING AND NEIGHBORHOOD COMPLIANCE  
DEPARTMENT (BNC)  
BOARD AND CODE ADMINISTRATION DIVISION**

**MIAMI-DADE COUNTY  
PRODUCT CONTROL SECTION**

11805 SW 26 Street, Room 208  
Miami, Florida 33175-2474  
T (786) 315-2590 F (786) 315-2599  
[www.miamidade.gov/building](http://www.miamidade.gov/building)

**NOTICE OF ACCEPTANCE (NOA)**

**Firestone Building Products Company  
250 West 96<sup>th</sup> Street  
Indianapolis, IN 46260**

**SCOPE:**

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County BNC - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. BNC reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code and the High Velocity Hurricane Zone of the Florida Building Code.

**DESCRIPTION: Firestone UltraPly TPO & TPO XR Single Ply Roof Systems over Steel Decks**

**LABELING:** Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

**RENEWAL** of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

**TERMINATION** of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

**ADVERTISEMENT:** The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

**INSPECTION:** A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA revises NOA No. 08-0118.05 and consists of pages 1 through 29.  
The submitted documentation was reviewed by Jorge L. Acebo.



NOA No.: 09-0902.12  
Expiration Date: 11/27/12  
Approval Date: 04/14/11  
Page 1 of 29

## ROOFING SYSTEM APPROVAL

<b>Category:</b>	Roofing
<b>Sub-Category:</b>	Single Ply Roofing
<b>Material:</b>	TPO
<b>Deck Type:</b>	Steel
<b>Maximum Design Pressure</b>	-150 psf

### TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specifications</u>	<u>Product Description</u>
UltraPly TPO	Various	TAS 131-95	Reinforced TPO 0.045" to 0.080" thick membrane
UltraPly TPO XR 100	Various	TAS 131-95	Reinforced Fleece-backed TPO
UltraPly TPO XR 115	Various	TAS 131-95	Reinforced Fleece-backed TPO
TPO QuickSeam Flashing	5-3/4" x 100'	TAS 131-95	Flashing material with pre-applied adhesive
UltraPly QuickSeam R.M.A. Strip	10" x 100'		Strip of UltraPly TPO with QuickSeam Tape for anchoring membrane to substrate
Single-Ply QuickPrime	1 gallon & # gallon	Proprietary	Primer for TPO QuickSeam Flashing
EdgeGard System	Various	Various	Flashing materials and assemblies
UltraPly Bonding Adhesive	5 gal. pail	Proprietary	Solvent based adhesive
Firestone I.S.O Stick Adhesive	5 gal	Proprietary	A dual component polyurethane adhesive.
Firestone I.S.O Twin Pack	5 gal	Proprietary	A dual component polyurethane adhesive.
Firestone I.S.O Fix II Adhesive	5 gal	Proprietary	A single component polyurethane adhesive.

### APPROVED INSULATIONS:

TABLE 2

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
ISO 95+ GL	Polyisocyanurate foam insulation	Firestone Bldg. Pro. Co.
FiberTop E	Wood fiber insulation board	Firestone Bldg. Pro. Co.
ISOGARD HD	Polyisocyanurate with a coated fiberglass facer	Firestone Bldg. Pro. Co.
ISOGARD HD Composite	Polyisocyanurate with a coated fiberglass facer composite insulation.	Firestone Bldg. Pro. Co.
High Density Wood Fiberboard	Non-Asphaltic fiberboard Insulation	Generic



NOA No.: 09-0902.12  
 Expiration Date: 11/27/12  
 Approval Date: 04/14/11  
 Page 2 of 29

**APPROVED INSULATIONS:**

**TABLE 2**

<b>Product Name</b>	<b>Product Description</b>	<b>Manufacturer (With Current NOA)</b>
Sturdi-Top/High Density Wood Fiber	Non-Asphaltic fiberboard Insulation	Georgia-Pacific
DensDeck, DensDeck Prime	Silicon treated gypsum	G-P Products

**APPROVED FASTENERS:**

**TABLE 3**

<b>Fastener Number</b>	<b>Product Name</b>	<b>Product Description</b>	<b>Dimensions</b>	<b>Manufacturer (With Current NOA)</b>
1.	Firestone HD Fastener	#15 Fastener for steel, Wood, concrete decks	N/A	Firestone Bldg. Pro. Co.
2.	Firestone AP Fastener	#14 Fastener for steel, Wood, concrete decks	N/A	Firestone Bldg. Pro. Co.
3.	UltraPly TPO 2-3/8" Barbed Seam Plate	Membrane seam attachment plate	2-3/8" diameter	Firestone Bldg. Pro. Co.
4.	Pre-Assembled AP fastener & plate	#14 w/insulation plate for steel, Wood, concrete decks	N/A	Firestone Bldg. Pro. Co.
5.	Pre-Assembled HD fastener & plate	#15 w/insulation plate for steel, Wood, concrete decks	N/A	Firestone Bldg. Pro. Co.
6.	Firestone HD Plus Fastener	Insulation and membrane fastener	Various	Firestone Bldg. Pro. Co.
7.	Firestone Insulation Fastening Plate	Galvalume insulation plate	3" diameter	Firestone Bldg. Pro. Co.
8.	Firestone HD HailGard Fasteners	Insulation and membrane fasteners	Various	Firestone Bldg. Pro. Co.
9.	HD Seam Plates	AZ55 or AZ50 galvalume insulation plate.	2-3/8" diameter	Firestone Bldg. Pro. Co.
10.	Firestone HD Plus Seam Plate	Galvalume insulation plate	2 3/4" diameter	Firestone Bldg. Pro. Co.
11.	Firestone Metal Batten Bar	Galvalume AZ55 batten strip	10' long, 1" wide	Firestone Bldg. Pro. Co.
12.	Firestone Coiled Metal Batten Bar	Galvalume AZ55 batten strip	220' long, 1" wide	Firestone Bldg. Pro. Co.
13.	Firestone Polymer Batten Strips	Polymer, corrosion --free, batten strip.	250' long, 3/4" or 1" wide	Firestone Bldg. Pro. Co.



**EVIDENCE SUBMITTED:**

<u>Test Agency</u>	<u>Test Identifier</u>	<u>Description</u>	<u>Date</u>
Underwriters Laboratories Inc.	01NK17982	UL790	06/05/01
	00NK43467	UL790	01/22/01
	99NK5401	UL790	08/17/99
	99NK3276	UL790	03/30/99
	98NK39140	UL790	05/13/99
	03NK34486	UL790	03/22/05
	Factory Mutual Research Corporation	3006983	4470
3004249		4470	11/03/99
3003830		4470	05/26/99
3001925		4470	05/24/99
3014031		4470	07/22/02
3014918		4470	12/17/03
3012931		4470	04/04/04
3016670		4470	04/29/04
3017120		4470	04/30/04
3020394		4470	09/03/04
3022988		4470	01/28/05
3029384		4470	02/28/08
3027508		4470	02/07/07
3026519		4470	12/14/06
3026520		4470	12/14/06
3030650		4470	05/16/08
3019991		4470	09/20/05
3033218		4470	08/12/08
3030227		4470	06/18/07
3033921		4470	01/12/09
3035560	4470	01/11/10	
Trinity ERD	F8960.04.08	TAS 114-F	04/15/08
	F8300.11.08-R3	TAS 131/ ASTM D6878	02/25/11

**APPROVED ASSEMBLIES:**

- Membrane Type:** Single Ply, Thermoplastic, TPO
- Deck Type 2I:** Steel, Insulated
- Deck Description:** 22 ga., Type B, Grade 33 steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (two fastener installed at each bearing attachment point) and Traxx 1 fasteners 12" o.c. at the side laps.
- System Type B:** Membrane fully adhered over mechanically fastened insulation. Side laps are sealed with a min 1.5" heat weld.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 2" thick</b>	<b>1 or 2 with 7</b>	<b>1:1 ft<sup>2</sup></b>
<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD Minimum ½" thick</b>	<b>N/A</b>	<b>N/A</b>

**Note:** Base layer shall be mechanically attached with fasteners and density described. Top layer of insulation shall be adhered to base insulations with Firestone I.S.O. Twin Pack Insulation Adhesive in continuous ½" – ¾" wide beads spaced 12" o.c. or Firestone I.S.O. FIX II Adhesive or I.S.O. Stick Adhesive Fastener applied in continuous ¾" – 1" wide ribbons spaced 12" o.c. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the top insulation layer with Firestone UltraPly Bonding Adhesive applied to both the substrate and the underside of the roof cover for a combined rate of 120 ft<sup>2</sup>/gal. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design**

**Pressure:** -90.0 psf (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced  
**Deck Type 2I:** Steel, Insulated  
**Deck Description:** Minimum 22 gauge Grade C steel deck secured to supports space a maximum 6' o.c. with ITW Buildex Traxx/5 spaced 6" o.c. Side laps fastened with ITW Buildex Traxx/1 spaced 24" o.c.  
**System Type C(1):** All layers of insulation simultaneously attached, membrane fully adhered.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL</b>		
<b>Minimum 1.5" thick</b>	N/A	N/A

**Note:** All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>Plywood</b>		
<b>Minimum 19/32" thick</b>	1&7 or 2&7	1:2 ft <sup>2</sup>

**Barrier:** None.

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -75 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga. steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (two fasteners installed at each bearing attachment point) and Traxx 1 fasteners 12" o.c. at the side laps.

**System Type C(2):** All layers of insulation simultaneously attached; membrane fully adhered.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A

**Note:** All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>Plywood Minimum 19/32" thick</b>	1&7 or 5	1:1 ft <sup>2</sup>

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -150 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga. steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (two fasteners installed at each bearing attachment point) and Traxx 1 fasteners 24" o.c. at the side laps

**System Type C(3):** All layers of insulation simultaneously attached; membrane fully adhered.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.2" thick</b>	N/A	N/A

**Note: All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.**

<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>Plywood Minimum 19/32" thick</b>	8	1:1.6 ft <sup>2</sup>

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -52.5 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga. steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners and 3/4" washers spaced 6" o.c. (two fasteners installed at each bearing attachment point) and Traxx 1 fasteners 12" o.c. at the side laps

**System Type C(4):** All layers of insulation simultaneously attached; membrane fully adhered.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

**Base Insulation Layer**

**Insulation Fasteners  
(Table 3)**

**Fastener  
Density/ft<sup>2</sup>**

**ISO 95+ GL**

**Minimum 1.5" thick**

N/A

N/A

**Note: All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.**

**Top Insulation Layer (cover board)**

**Insulation Fasteners  
(Table 3)**

**Fastener  
Density/ft<sup>2</sup>**

**DensDeck Prime**

**Minimum 1/2" thick**

**1&7 or 5 or 2&7**

**1:1.33 ft<sup>2</sup>**

**Membrane:**

Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design**

**Pressure:** -75 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22 gauge, Type B steel deck secured to ¼” steel structural supports spaced a maximum 6ft o.c. secured with ITW Buildex Traxx 5 fasteners spaced maximum 6” o.c. at supports. Side laps, secured 24” o.c. with ITW Buildex TRAXX 1 fasteners.

**System Type C(5):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5” thick</b>	<b>2&amp;7 or 4</b>	<b>1:1.33 ft<sup>2</sup></b>

**Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.**

**Membrane:** Firestone UltraPly TPO membrane fully adhered to insulation with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design  
Pressure:** -90 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced  
**Deck Type 2I:** Steel, Insulated  
**Deck Description:** 22 gauge, Type B steel deck attached to 1/4" steel structural supports spaced a maximum 6ft o.c. secured with ITW Buildex Traxx 5 fasteners spaced maximum 6" o.c. at supports. Side laps, secured 24" o.c. with ITW Buildex TRAXX 1 fasteners.  
**System Type C(6):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 2" thick</b>	<b>1&amp;7 or 4</b>	<b>1:1.6 ft<sup>2</sup></b>

**Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.**

**Membrane:** Firestone UltraPly TPO membrane fully adhered to insulation with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -75 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22 ga., Type B, Grade 33 steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (one fastener installed at each bearing attachment point) and Traxx 1 fasteners 24" o.c. at the side laps.

**System Type C(7):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A

**Note:** All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD Minimum ½" thick</b>	1&7 or 2&7	1: 1.33 ft <sup>2</sup>

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the top insulation layer with Firestone UltraPly Bonding Adhesive applied to both the substrate and the underside of the roof cover for a combined rate of 120 ft<sup>2</sup>/gal. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -60 psf (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22 ga., Type B, Grade 33 steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (one fastener installed at each bearing attachment point) and Traxx 1 fasteners 24" o.c. at the side laps.

**System Type C(8):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL</b> Minimum 1.5" thick	N/A	N/A

**Note: All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.**

<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD</b> Minimum 1" thick	1&7 or 2&7	1: 1.8 ft <sup>2</sup>

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the top insulation layer with Firestone UltraPly Bonding Adhesive applied to both the substrate and the underside of the roof cover for a combined rate of 120 ft<sup>2</sup>/gal. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -45 psf (See General Limitation #7)



**Membrane Type:** Single Ply, Thermoplastic, TPO

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22ga., Type B, Grade 33 Steel Deck secured to ¼” thick supports spaced maximum 6 ft o.c. with Traxx/5 fasteners spaced 6”o.c. at supports (two fasteners at each bearing attachment point). Side laps secured with Traxx/1 fasteners at 24”o.c.

**System Type C(9):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 2” thick</b>	<b>1&amp;7 or 2&amp;7</b>	<b>1:1 ft<sup>2</sup></b>

**Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).**

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressures:** -112.5 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, Thermoplastic, TPO

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22ga., Grade 80 Steel Deck secured to ¼” thick supports spaced maximum 6 ft o.c. with Traxx/5 fasteners spaced 6”o.c. at supports (two fasteners at each bearing attachment point). Side laps secured with Traxx/1 fasteners at 24”o.c.

**System Type C(10):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 2” thick</b>	<b>1&amp;7 or 2&amp;7</b>	<b>1:1 ft<sup>2</sup></b>

**Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).**

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressures:** -150 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, Thermoplastic, TPO  
**Deck Type 2I:** Steel, Insulated  
**Deck Description:** 22 ga., Type B, Grade 33 steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (one fastener installed at each bearing attachment point) and Traxx 1 fasteners 24" o.c. at the side laps.  
**System Type C(11):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD Composite Minimum 1" thick</b>	<b>1&amp;7 or 2&amp;7</b>	<b>1: 1.33 ft<sup>2</sup></b>

**Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.**

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the top insulation layer with Firestone UltraPly Bonding Adhesive applied to both the substrate and the underside of the roof cover for a combined rate of 120 ft<sup>2</sup>/gal. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -60 psf (See General Limitation #7)



**Membrane Type:** Single Ply, Thermoplastic, TPO

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22 ga., Type B, Grade 33 steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (one fastener installed at each bearing attachment point) and Traxx 1 fasteners 24" o.c. at the side laps.

**System Type C(12):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD Composite Minimum 1.5" thick</b>	<b>1&amp;7 or 2&amp;7</b>	<b>1: 1.33 ft<sup>2</sup></b>

**Note:** Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the top insulation layer with Firestone UltraPly Bonding Adhesive applied to both the substrate and the underside of the roof cover for a combined rate of 120 ft<sup>2</sup>/gal. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -112.5 psf (See General Limitation #7)



**Membrane Type:** Single Ply, Thermoplastic, TPO

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 22 ga., Type B, Grade 33 steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. (one fastener installed at each bearing attachment point) and Traxx 1 fasteners 24" o.c. at the side laps.

**System Type C(13):** Membrane fully adhered over mechanically fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD Composite Minimum 2" thick</b>	<b>1&amp;7 or 2&amp;7</b>	<b>1: 1.33 ft<sup>2</sup></b>

**Note:** Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the top insulation layer with Firestone UltraPly Bonding Adhesive applied to both the substrate and the underside of the roof cover for a combined rate of 120 ft<sup>2</sup>/gal. The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -120 psf (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga. steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners and 3/4" washers spaced 6" o.c. (two fasteners installed at each bearing attachment point) and Traxx 1 fasteners 12" o.c. at the side laps

**System Type C(14):** All layers of insulation simultaneously attached; membrane fully adhered.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A

**Note:** All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

<b>Top Insulation Layer (cover board)</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>DensDeck Prime Minimum 1/2" thick</b>	<b>1&amp;7 or 5 or 2&amp;7</b>	<b>1:1 ft<sup>2</sup></b>

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -105 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced  
**Deck Type 2I:** Steel, Insulated  
**Deck Description:** Minimum 22 gauge Grade C steel deck secured to supports space a maximum 6' o.c. with ITW Buildex Traxx/5 spaced 6" o.c. Side laps fastened with ITW Buildex Traxx/1 spaced 24" o.c.  
**System Type C(15):** All layers of insulation simultaneously attached, membrane fully adhered.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISOGARD HD Composite Minimum 1.5" thick</b>	<b>1&amp;7 or 2&amp;7</b>	<b>1: 1.78 ft<sup>2</sup></b>

**Note: Insulation shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.**

**Barrier:** None.

**Membrane:** Firestone UltraPly TPO membrane fully adhered to the cover board with Firestone UltraPly Bonding Adhesive at a rate of 60 sq.ft./gal per side. (Coverage area is for adhesive application onto each of the two mating surfaces). The roof cover side and end laps are sealed with a minimum 1.5 in. heat weld.

**Maximum Design Pressure:** -60 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** Minimum 22 ga. Grade E steel deck secured to supports space at maximum 6 ft o.c. with ITW Buildex Traxx/5 spaced at 6" o.c. Side lap fastened with ITW Buildex Traxx/1 spaced at 24" o.c.

**System Type D(1):** Membrane mechanically attached over preliminary fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
ISO 95+ GL Minimum 1.5" thick	N/A	N/A
<b>(Optional) Top Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
DensDeck Minimum ¼" thick	N/A	N/A
FiberTop E, High Density Wood Fiber, Sturdi-Top/High Density Wood Fiber Minimum ½" thick	N/A	N/A

**Note:** All insulation shall have preliminary attachment, prior to the installation of the roofing membrane at a minimum application rate of two fasteners per board for insulation boards having no dimension greater than 4 ft., and four fasteners for any insulation board having no dimension greater than 8 ft.

**Barrier:** None.

**Membrane:** Firestone UltraPly TPO (45-80 mils) Reinforced Membrane attached to deck through the preliminary attached insulation as specified below.

**Fastening #1:** Membrane is mechanically attached using Firestone HD+ Fasteners and HD+Seam Plates spaced 12" o.c. within minimum 6" wide laps in rows 9'-6" o.c. Laps sealed with a minimum 5" wide hot air heat weld.  
*(Maximum Design Pressure:-45 psf; See General Limitation #7.)*

**Fastening #2:** Membrane is mechanically attached using Firestone HD Fasteners and 1" wide Metal Batten Bars centered within the 6" wide side laps. Fasteners spaced 6" o.c. along the batten bar. Batten bar rows were spaced 9'-6" o.c. Laps sealed with a minimum 5" wide hot air heat weld.  
*(Maximum Design Pressure:-75 psf; See General Limitation #7.)*



- Fastening #3:** Membrane is mechanically attached using Firestone HD Fasteners and 3/4" wide Polymer Batten Strips centered within the 6" wide side laps. Fasteners spaced 6" o.c. along the batten bar. Batten bar rows were spaced 9'-6" o.c. Laps sealed with a minimum 5" wide hot air heat weld.  
*(Maximum Design Pressure:-60 psf; See General Limitation #7.)*
- Fastening #4:** Membrane is mechanically attached using Firestone HD+ Fasteners and 3/4" wide Polymer Batten Strips centered within the 6" wide side laps. Fasteners spaced 6" o.c. along the batten bar. Batten bar rows were spaced 9'-6" o.c. Laps sealed with a minimum 5" wide hot air heat weld.  
*(Maximum Design Pressure:-75 psf; See General Limitation #7.)*
- Fastening #5:** Membrane is mechanically attached using Firestone HD Fasteners and HD Seam Plates 12" o.c. within minimum 6" wide laps. Laps are spaced 90" o.c. and sealed with minimum 1.5" heat weld.  
*(Maximum Design Pressure:-45 psf; See General Limitation #7.)*
- Fastening #6:** Membrane is mechanically attached using Firestone HD Plus Fasteners and HD Plus Seam Plates spaced 12" o.c. within minimum 6" wide laps. Laps are spaced a maximum 114" o.c. and sealed with minimum 1.5" heat weld.  
*(Maximum Design Pressure:-45 psf; See General Limitation #7.)*
- Fastening #7:** Membrane is mechanically attached using Firestone HD Plus Fasteners and HD Plus Seam Plates spaced 6" o.c. within minimum 6" wide laps. Laps are spaced at maximum 90" o.c. and sealed with minimum 5" heat weld.  
*(Maximum Design Pressure:-90 psf; See General Limitation #7.)*
- Fastening #8:** Membrane is mechanically attached using Firestone HD Plus Fastener and 1" Metal Battens centered with the minimum 6" wide laps. Fasteners are spaced 6" o.c. along the batten bars. Batten rows are spaced at maximum 90" o.c. and sealed with minimum 5" heat weld.  
*(Maximum Design Pressure:-97.5 psf; See General Limitation #7.)*
- Maximum Design Pressure:** See Fastening Options Above



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** Minimum 22 ga. Grade E steel deck secured to supports space at maximum 6 ft o.c. with ITW Buildex Traxx/5 spaced at 6" o.c. Side lap fastened with ITW Buildex Traxx/1 spaced at 24" o.c.

**System Type D(2):** Membrane mechanically attached over preliminary fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

**Base Insulation Layer**

**ISO 95+ GL**

**Minimum 2" thick**

**Insulation Fasteners  
(Table 3)**

**Fastener  
Density/ft<sup>2</sup>**

N/A

N/A

**(Optional) Top Insulation Layer**

**Insulation Fasteners  
(Table 3)**

**Fastener  
Density/ft<sup>2</sup>**

**DensDeck**

**Minimum ¼" thick**

N/A

N/A

**FiberTop E, High Density Wood Fiber, Sturdi-Top/High Density Wood Fiber**

**Minimum ½" thick**

N/A

N/A

**Note:** All insulation shall have preliminary attachment, prior to the installation of the roofing membrane at a minimum application rate of two fasteners per board for insulation boards having no dimension greater than 4 ft., and four fasteners for any insulation board having no dimension greater than 8 ft.

**Barrier:** None.

**Membrane:** Firestone UltraPly TPO (45-80 mils) Reinforced Membrane attached to deck through the preliminary attached insulation as specified below.

**Fastening:** Membrane is mechanically attached using Firestone HD Fasteners and HD Seam Plates spaced 6" o.c. within minimum 6" wide laps. Laps are spaced at maximum 14" o.c. and sealed with a minimum 1.5" wide heat weld.

**Maximum Design**

**Pressure:** -52.5 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced  
**Deck Type 2I:** Steel, Insulated  
**Deck Description:** Minimum 22 gauge Grade C steel deck secured to supports space at maximum 6 ft. o.c. with ITW Buildex Traxx/5 spaced 6" o.c. Side laps fastened with ITW Buildex Traxx/1 spaced 24" o.c.  
**System Type D(3):** Membrane mechanically attached over preliminary fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL</b>		
<b>Minimum 1.5" thick</b>	N/A	N/A
<b>(Optional) Top Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>DensDeck</b>		
<b>Minimum ¼" thick</b>	N/A	N/A
<b>FiberTop E, High Density Wood Fiber, Sturdi-Top/High Density Wood Fiber</b>		
<b>Minimum ½" thick</b>	N/A	N/A

**Note:** All insulation shall have preliminary attachment, prior to the installation of the roofing membrane at a minimum application rate of two fasteners per board for insulation boards having no dimension greater than 4 ft., and four (4) fasteners for any insulation board having no dimension greater than 8 ft.

**Barrier:** None.

**Membrane:** Firestone UltraPly TPO (45-80 mils) Reinforced Membrane attached through the preliminary attached insulation as described below.

**Fastening #1:** Membrane is mechanically attached using Firestone HD Plus Fasteners and HD Plus Seam Plates spaced 12" o.c. within minimum 6" wide laps. Laps are spaced at maximum 90" o.c. and sealed with a minimum 1.5" heat weld.  
*(Maximum Design Pressure:-45 psf; See General Limitation #7.)*

**Fastening #2:** Membrane is mechanically attached using Firestone HD Plus Fasteners and 1" metal batten centered within minimum 6" wide laps. Fasteners are spaced 6" o.c. along the batten bar. Batten bar rows are spaced 90" o.c. and sealed with a minimum 5" heat weld.  
*(Maximum Design Pressure:-82.5 psf; See General Limitation #7.)*

**Fastening #3:** Membrane is mechanically attached using Firestone HD Plus Fasteners and HD Plus Seam Plates spaced 6" o.c. within minimum 6" wide laps. Laps are spaced at maximum 90" o.c. and sealed with a minimum 5" heat weld.  
*(Maximum Design Pressure:-82.5 psf; See General Limitation #7.)*

**Maximum Design Pressure:** See Fastening Options Above



**Membrane Type:** Single Ply, TPO, Reinforced  
**Deck Type 2I:** Steel, Insulated  
**Deck Description:** 18-22 ga. steel deck is secured to supports spaced 6 ft. o.c. with Traxx 5 fasteners spaced 6" o.c. and Traxx 1 fasteners 24" o.c. at the side laps  
**System Type D(4):** Membrane mechanically attached over preliminary fastened insulation.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A

**Note: All layers of insulation and membrane shall be simultaneously attached. See membrane below for fasteners and density. Refer to Roofing Application Standard RAS 117 for insulation attachment requirements. Insulation shall have preliminary attachment, prior to the installation of the roofing membrane.**

**Membrane:** Mechanically attach Firestone UltraPly QuickSeam R.M.A. Strips with Firestone Heavy Duty Fasteners 6" o.c. in Firestone Coiled Metal Batten Strip centered within the 4" wide center section of the UltraPly QuickSeam R.M.A Strips in rows 10 ft. o.c. Firestone UltraPly TPO roof cover is adhered to the UltraPly QuickSeam R.M.A. Strips by first priming the underside of the roof cover, at the strip locations, with Firestone Single-Ply QuickPrime and placing the primed portion of the roof cover onto the strips. Minimum 2" wide side laps are sealed with a minimum 1.5" wide heat weld.

Or mechanically attach Firestone UltraPly TPO membrane with Firestone HD Plus fasteners 12" o.c. in Firestone ¾" or 1" Polymer Batten Strip centered within the 6" wide side laps in rows 9-½ ft. o.c. The roof cover laps are sealed with a minimum 5" heat weld.

**Maximum Design Pressure:** -45 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga., type B steel decking attached to steel supports spaced 6 ft. o.c. using Traxx 5 fasteners spaced 6" o.c. (at the bottom flute) two fasteners at each bearing attachment point, and with side laps attached using Traxx 1 fasteners spaced 14" o.c.

**System Type D(5):** All layers of insulation and base sheet simultaneously attached.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Base Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A
<b>Top Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>DensDeck or DensDeck Prime Minimum ½" thick</b>	N/A	N/A

**Note:** All layers of insulation and membrane shall be simultaneously attached. See membrane below for fasteners and density. Refer to Roofing Application Standard RAS 117 for insulation attachment requirements. Insulation shall have preliminary attachment, prior to the installation of the roofing membrane.

**Membrane:** Firestone UltraPly TPO mechanically fastened to the deck through the insulation as described below:

**Fastening:** Firestone Heavy-Duty Plus fasteners spaced 6 in. o.c. along 1" wide Firestone Coiled Metal Batten Strip centered within the 6 in. wide laps spaced 4-½ ft. o.c. The roof cover side laps are sealed with a minimum 5 in. wide heat weld.

**Maximum Design Pressure:** -112.5 psf; (See General Limitation #7)



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga., type B steel decking attached to steel supports spaced 6 ft. o.c. using Traxx 5 fasteners spaced 6" o.c. (at the bottom flute), and with side laps attached using Traxx 1 fasteners spaced 24" o.c.

**System Type D(6):** All layers of insulation and base sheet simultaneously attached.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A

**Note:** All layers of insulation and membrane shall be simultaneously attached. See membrane below for fasteners and density. Refer to Roofing Application Standard RAS 117 for insulation attachment requirements. Insulation shall have preliminary attachment, prior to the installation of the roofing membrane.

**Membrane:** Firestone UltraPly TPO mechanically fastened to the deck through the insulation as described below:

**Fastening #1:** Membrane is mechanically attached using Firestone HD Plus Fasteners and HD Plus Seam Plates spaced 6" o.c. within minimum 6" wide laps. Laps are spaced at maximum 142" o.c. and sealed with a minimum 1.5" heat weld.  
*Maximum Design Pressure: -60 psf; (See General Limitation #7)*

**Fastening #2:** Membrane is mechanically attached using Firestone HD Plus Fasteners and 1" wide Firestone Coiled Metal Batten Strip with fasteners spaced 6" o.c. along the batten bar within minimum 6" wide laps. Laps are spaced at maximum 142" o.c. and sealed with a minimum 5" wide heat weld that encapsulates the fasteners and batten strip.  
*Maximum Design Pressure: -60 psf; (See General Limitation #7)*

**Fastening #3:** Membrane is mechanically attached using Firestone HD Plus Fasteners and HD Plus Seam Plates spaced 6" o.c. within minimum 6" wide laps. Laps are spaced at maximum 114" o.c. and sealed with a minimum 1.5" heat weld.  
*Maximum Design Pressure: -67.5 psf; (See General Limitation #7)*

**Fastening #4:** Membrane is mechanically attached using Firestone HD Plus Fasteners and 1" wide Firestone Coiled Metal Batten Strip with fasteners spaced 6" o.c. along the batten bar within minimum 6" wide laps. Laps are spaced at maximum 114" o.c. and sealed with a minimum 5" wide heat weld that encapsulates the fasteners and batten strip.  
*Maximum Design Pressure: -67.5 psf; (See General Limitation #7)*

**Maximum Design Pressure:** See Fastening Options Above



**Membrane Type:** Single Ply, TPO, Reinforced

**Deck Type 2I:** Steel, Insulated

**Deck Description:** 18-22 ga., Grade 80 steel decking attached to steel supports spaced 6 ft. o.c. using Traxx 5 fasteners spaced 6" o.c. (at the bottom flute), and with side laps attached using Traxx 1 fasteners spaced 24" o.c.

**System Type D(7):** All layers of insulation and base sheet simultaneously attached.

**All General and System Limitations apply.**

One or more layers of any of the following insulations.

<b>Insulation Layer</b>	<b>Insulation Fasteners (Table 3)</b>	<b>Fastener Density/ft<sup>2</sup></b>
<b>ISO 95+ GL Minimum 1.5" thick</b>	N/A	N/A

**Note: All layers of insulation and membrane shall be simultaneously attached. See membrane below for fasteners and density. Refer to Roofing Application Standard RAS 117 for insulation attachment requirements. Insulation shall have preliminary attachment, prior to the installation of the roofing membrane.**

**Membrane:** Firestone UltraPly TPO mechanically fastened to the deck through the insulation as described below:

**Fastening #1:** Membrane is mechanically attached using Firestone HD Fasteners and HD Seam Plates spaced 6" o.c. within minimum 6" wide laps. Laps are spaced at maximum 142" o.c. and sealed with a minimum 1.5" heat weld.  
*Maximum Design Pressure: -52.5 psf; (See General Limitation #7)*

**Fastening #2:** Membrane is mechanically attached using Firestone HD Fasteners and 1" wide Firestone Coiled Metal Batten Strip with fasteners spaced 6" o.c. along the batten bar within minimum 6" wide laps. Laps are spaced at maximum 142" o.c. and sealed with a minimum 5" wide heat weld that encapsulates the fasteners and batten strip.  
*Maximum Design Pressure: -52.5 psf; (See General Limitation #7)*

**Fastening #3:** Membrane is mechanically attached using Firestone HD Plus Fasteners and Firestone ¾" or 1" Polymer Batten Strips with fasteners spaced 6" o.c. along the batten bar in rows spaced 142" o.c. and along one intermediate field row centered in the field of the sheet. Side laps are sealed with a minimum 5" heat weld and the intermediate field row is covered with a minimum 5" wide strip of UltraPly TPO and sealed with a minimum 1.5" heat weld on either side of the batten.  
*Maximum Design Pressure: -135 psf; (See General Limitation #7)*

**Fastening #4:** Membrane is mechanically attached using Firestone HD Fasteners and Firestone ¾" or 1" Polymer Batten Strips with fasteners spaced 6" o.c. along the batten bar within minimum 6" wide laps. Laps are spaced at maximum 68" o.c. and sealed with a minimum 5" wide heat weld that encapsulates the fasteners and batten strip.  
*Maximum Design Pressure: -82.5 psf; (See General Limitation #7)*

**Maximum Design Pressure:** See Fastening Options Above



## STEEL DECK SYSTEM LIMITATIONS:

1. If mechanical attachment to the structural deck through the lightweight insulating concrete is proposed, a field withdrawal resistance testing shall be performed to determine equivalent or enhanced fastener patterns and density. All testing and fastening design shall be in compliance with Testing Application Standard TAS 105 and Roofing Application Standard RAS 117 and/or RAS 137, calculations shall be signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant.
2. For steel deck application where specific deck construction is not referenced: The deck shall be a minimum 22 gage attached with 5/8" puddle welds with weld washers at every flute with maximum deck spans of 5 ft. o.c.

## GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance; refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer.
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each side lap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq.

**Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**

5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. Insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117 and/or RAS 137. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform to Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 9B-72 of the Florida Administrative Code.

**END OF THIS ACCEPTANCE**



NOA No.: 09-0902.12  
Expiration Date: 11/27/12  
Approval Date: 04/14/11  
Page 29 of 29