



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)
BOARD AND CODE ADMINISTRATION DIVISION

NOTICE OF ACCEPTANCE (NOA)

MIAMI-DADE COUNTY
PRODUCT CONTROL SECTION

11805 SW 26 Street, Room 208
Miami, Florida 33175-2474
T (786)315-2590 F (786) 31525-99

www.miamidade.gov/economy

GenFlex Roofing Systems

A Division of Firestone Building Products Company, LLC

200 4th Ave. South
Nashville, TN 37201

SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

DESCRIPTION: GenFlex EZ TPO SA Single Ply Roof Systems over Wood Decks.

LABELING: Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

RENEWAL of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

TERMINATION of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

ADVERTISEMENT: The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

INSPECTION: A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This renews and revises NOA No. 15-0428.17 and consists of pages 1 through 17.
The submitted documentation was reviewed by Hamley Pacheco, P.E.



NOA No.: 19-1205.04
Expiration Date: 12/17/25
Approval Date: 03/12/20
Page 1 of 17

ROOFING SYSTEM APPROVAL

Category: Roofing
Sub-Category: Single Ply Roofing
Material: EX TPO Peel and Stick HW
Deck Type: Wood
Maximum Design Pressure: -67.5 psf.

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specifications</u>	<u>Product Description</u>
EZ TPO Peel and Stick HW	Various	TAS 131 ASTM D6878	Reinforced TPO peel and stick membrane
TPO Reinforced Curb Corner	Various	TAS 131 ASTM D6878	TPO curb flashing
18" Curb Flashing	Various	TAS 131 ASTM D6878	TPO curb flashing
TPO Inside/Outside Corner	Various	TAS 131 ASTM D6878	Molded TPO for corner flashing
TPO Large Pipe Flashing	Various	TAS 131 ASTM D6878	TPO flashing for large round penetrations
TPO T-Joint Cover	Various	TAS 131 ASTM D6878	TPO flashing for T-joints
TPO Penetration Kit	Various	TAS 131 ASTM D6878	Penetration sealing kit for UltraPly TPO
TPO Walkway Pad	Various	TAS 131 ASTM D6878	TPO walkway pad
TPO Coated Metal	Various	TAS 131 ASTM D6878	TPO laminated to hot-dipped galvanized steel for flashing
TPO Premium Walkway Pad	Various	TAS 131 ASTM D6878	TPO walkway pad
TPO Reinforced Split Pipe Boot	Various	TAS 131 ASTM D6878	TPO flashing for round penetrations 1" to 9" in diameter
TPO 8" Reinforced Cover Strip	Various	TAS 131 ASTM D6878	8" wide 60 mil TPO cover strip
TPO Universal Pipe Boot	Various	TAS 131 ASTM D6878	TPO flashing for round penetrations 1" to 6" in diameter
TPO Unsupported Flashing	Various	TAS 131 ASTM D6878	Unreinforced TPO used for flashing
I.S.O. Twin Pack Insulation Adhesive	750 ml cartridges	Proprietary	A two-component polyurethane insulation adhesive.
I.S.O. Fix II	30 lbs.	Proprietary	A single component polyurethane insulation adhesive.
I.S.O. Stick	5 gal.	Proprietary	A two-component polyurethane insulation adhesive.
Quick Dual	Part 1 and Part	Proprietary	A two-component, low-rise



NOA No.: 19-1205.04
 Expiration Date: 12/17/25
 Approval Date: 03/12/20
 Page 2 of 17

<u>Product</u>	<u>Dimensions</u>	<u>Test Specifications</u>	<u>Product Description</u>
I.S.O. Spray R	2 15gal pail & 55gal drum	Proprietary	polyurethane adhesive A two-part polyurethane adhesive

APPROVED INSULATIONS:

TABLE 2

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
GenFlex ISO Insulation, GenFlex ISO Insulation Tapered	Polyisocyanurate foam insulation	GenFlex Roofing Systems
GenFlex HD ISO	Polyisocyanurate with a coated fiberglass facer	GenFlex Roofing Systems
GenFlex HD Composite ISO	Polyisocyanurate with a coated fiberglass facer composite insulation.	Genflex Roofing Systems
DensDeck Prime	Silicon treated gypsum	Georgia Pacific Gypsum LLC
Coated Glass Facer, Coated Glass Facer tapered	Polyisocyanurate foam core laminated to a coated fiberglass facer.	Genflex Roofing Systems
SECUROCK Gypsum-Fiber Roof Board	Rigid, gypsum-based board stock	USG Corp.

APPROVED FASTENERS:

TABLE 3

<u>Fastener Number</u>	<u>Product Name</u>	<u>Product Description</u>	<u>Dimensions</u>	<u>Manufacturer (With Current NOA)</u>
1.	Firestone Heavy-Duty	#15 Fastener for steel, Wood, concrete decks.	N/A	Firestone Bldg. Products
2.	Firestone All-Purpose	#14 Fastener for steel, Wood, concrete decks.	N/A	Firestone Bldg. Products
3.	Insulation Fastening Plate	Galvalume insulation plate. 3" diameter		Firestone Bldg. Products



EVIDENCE SUBMITTED:

<u>Test Agency</u>	<u>Test Identifier</u>	<u>Description</u>	<u>Date</u>
Underwriters Laboratories Inc.	UL R9516	UL 790	09/29/14
FM Approvals	3052525	FM 4470	02/20/15
PRI Construction Materials Technologies, LLC	FBP-208-02-01	TAS 131/ASTM D6878	04/16/15
	FBP-213-02-01	TAS 114 J	11/20/14
	FBP-165-02-01A	FM4474 D/TAS 114 J	04/28/14
	FBP-220-02-01.1	TAS 114 J	01/29/15
	FBP-230-02-01	TAS 114 J	04/02/15
	FBP-233-02-01	TAS 114 J	06/01/15
	FBP-233-02-02	TAS 114 C	04/03/15
	FBP-239-02-01	TAS 114 J	07/15/15
	FBP-358-02-01	FM4474 D/TAS 114 J	09/08/17
	FBP-359-02-01	FM4474 D/TAS 114 J	09/13/17
	FBP-362-02-01	FM4474 D/TAS 114 J	09/13/17
	FBP-044-02-01.11	TAS 114 D, H, J	09/23/19
		TAS 117 A, B	
		ASTM D1876 & D903	
	FBP-063-02-01	TAS 114 E	07/12/12



APPROVED ASSEMBLIES:

Membrane Type:	Single Ply, TPO, Reinforced
Deck Type 1I:	Wood, Insulated
Deck Description:	Minimum 15/32" plywood attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.
System Type B(1):	Base layer of insulation mechanically attached, top layer adhered with approved adhesive. Membrane fully adhered.

All General and System Limitations apply.

One or more layers of any of the following insulations.

<u>Base Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
GenFlex ISO Insulation, Coated Glass Facer Minimum ½" thick	NA	NA
<u>Middle Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
GenFlex ISO Insulation, Coated Glass Facer Minimum 1.5" thick	1 or 2 with 3	1:1.33 ft ²

Note: Base layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).

<u>Top Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
SECUROCK Gypsum Fiber Roof Board, DensDeck Prime Minimum ¼" thick	N/A	N/A
GenFlex HD ISO Minimum ½" thick	N/A	N/A
GenFlex HD Composite ISO Minimum 1.5" thick	N/A	N/A

Note: Top layer of insulation shall be adhered with I.S.O. Twin Pack Insulation Adhesive applied in ¾" wide ribbons spaced 12" o.c. or with I.S.O. Fix II, I.S.O. Spray R, or I.S.O. Stick applied in ¾" to 1" wide ribbons spaced 12" o.c. or with Quick Dual applied in 1" to 1.25" wide ribbons spaced 12" o.c. Please refer to Roofing Application Standard RAS 117 for insulation attachment. Composite insulation boards used as a top layer shall be installed with the polyisocyanurate face down.

Membrane:	Min. 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.
Maximum Design Pressures:	-75 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 15/32" plywood (19/32" for new construction) attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.

System Type C(1): Membrane fully adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
One or more layers of any of the following insulations:		
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
DensDeck Prime, SECUROCK Gypsum-Fiber Roof Board Minimum 1/4" thick	1 or 2 with 3	1:1.78 ft ²
Coated Glass Facer Minimum 1" thick	1 or 2 with 3	1:1.78 ft ²
GenFlex ISO Insulation Minimum 1.5" thick	1 or 2 with 3	1:1.78 ft ²

Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Min. 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -45 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 15/32" plywood (19/32" for new construction) attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.

System Type C(2): Membrane fully adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex HD Composite ISO Minimum 1-1/2" thick	1 or 2 with 3	1:2.67 ft ²

Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Minimum 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -45 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 19/32" plywood

System Type C(3): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
DensDeck Prime, SECUROCK Gypsum Fiber Roof Board Minimum 1/2" thick	1 or 2 with 3	1:2.67 ft ²
GenFlex HD Composite ISO Minimum 1-1/2" thick	1 or 2 with 3	1:2.67 ft ²
Coated Glass Facer Minimum 2" thick	1 or 2 with 3	1:2.67 ft ²

Note: Base Insulation layer shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Min. 60 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -52.5 psf. (See General Limitation #9)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 15/32" plywood (19/32" for new construction) attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.

System Type C(4): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
SECUROCK Gypsum Fiber Roof Board Minimum 1/2" thick	1 or 2 with 3	1:2.13 ft ²
GenFlex HD Composite ISO Minimum 1-1/2" thick	1 or 2 with 3	1:2.13 ft ²

Note: Base Insulation layer shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Min. 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 3" wide side laps.

Maximum Design Pressures: -52.5 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 15/32" plywood (19/32" for new construction) attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.

System Type C(5): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
Coated Glass Facer Minimum 1-1/2" thick	1 or 2 with 3	1:1.78 ft ²
DensDeck Prime Minimum 1/2" thick	1 or 2 with 3	1:1.78 ft ²
GenFlex ISO Insulation Minimum 2" thick	1 or 2 with 3	1:1.78 ft ²

Note: Base Insulation shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Minimum 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -60 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 19/32" plywood

System Type C(6): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
GenFlex HD ISO Minimum 1/2" thick	1 or 2 with 3	1:2.13 ft ²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1" thick	1 or 2 with 3	1:2.13 ft ²
DensDeck Prime, SECUROCK Gypsum-Fiber Roof Board Minimum 1/4" thick	1 or 2 with 3	1:2.13 ft ²
GenFlex HD Composite ISO Minimum 1.5" thick	1 or 2 with 3	1:2.13 ft ²

Note: Base Insulation layer shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Minimum 60 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -55 psf. (See General Limitation #9)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type II: Wood, Insulated

Deck Description: Minimum 15/32" plywood (19/32" for new construction) attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.

System Type C(7): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum 1/2" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
SECUROCK Gypsum Fiber Roof Board Minimum 1/2" thick	1 or 2 with 3	1:1.78 ft ²
GenFlex HD Composite ISO Minimum 1-1/2" thick	1 or 2 with 3	1:1.78 ft ²

Note: Base Insulation layer shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Min. 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -67.5 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type 1I: Wood, Insulated

Deck Description: Minimum 15/32" plywood attached to structural supports spaced a maximum 24" o.c. with #8 x 2" wood screws spaced 6" o.c.

System Type C(8): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum ½" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
SECUROCK Gypsum Fiber Roof Board Minimum ½" thick	1 or 2 with 3	1:1.33 ft ²
GenFlex HD Composite ISO Minimum 1.5" thick	1 or 2 with 3	1:1.33 ft ²

Note: Base Insulation layer shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Minimum 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -82.5 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type 1I: Wood, Insulated

Deck Description: Minimum 15/32" plywood attached to structural supports spaced a maximum 24" o.c. with #8 x 2" wood screws spaced 6" o.c.

System Type C(9): Membrane self-adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum ½" thick	NA	NA
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density Density/ft²
DensDeck Prime Minimum ½" thick	1 or 2 with 3	1:1.33 ft ²
Coated Glass Facer Minimum 2" thick	1 or 2 with 3	1:1.33 ft ²

Note: Base Insulation layer shall be loose laid and top Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Minimum 60 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -75 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type 1I: Wood, Insulated

Deck Description: Minimum 15/32" plywood attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c. at the perimeter and 12" o.c. in the field of each board.

System Type C(10): Membrane fully adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum ½" thick	NA	NA
One or more layers of any of the following insulations:		
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
SECUROCK Gypsum-Fiber Roof Board Minimum ¼" thick	1 or 2 with 3	1:1.6 ft ²
DensDeck Prime Minimum ½" thick	1 or 2 with 3	1:1.6 ft ²
Coated Glass Facer Minimum 1" thick	1 or 2 with 3	1:1.6 ft ²
GenFlex ISO Insulation, GenFlex HD Composite ISO Minimum 1.5" thick	1 or 2 with 3	1:1.6 ft ²

Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Min. 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -45 psf. (See General Limitation #7)



Membrane Type: Single Ply, TPO, Reinforced

Deck Type 1I: Wood, Insulated

Deck Description: Minimum 15/32" plywood attached to structural supports spaced a maximum 24" o.c. with 0.113" ring shank nails spaced 6" o.c.

System Type C(11): Membrane fully adhered over mechanically fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
GenFlex ISO Insulation, Coated Glass Facer Minimum ½" thick	NA	NA
One or more layers of any of the following insulations:		
Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
DensDeck Prime, SECUROCK Gypsum-Fiber Roof Board Minimum ½" thick	1 or 2 with 3	1:1.6 ft ²
Coated Glass Facer Minimum 1" thick	1 or 2 with 3	1:1.6 ft ²
GenFlex ISO Insulation, GenFlex HD Composite ISO Minimum 1.5" thick	1 or 2 with 3	1:1.6 ft ²

Note: Insulation layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density. See Roofing Application Standard RAS 117 for fastening details.

Membrane: Min. 45 mil EZ TPO Peel and Stick HW self-adhered with 1.5" wide heat weld at the 2" wide side laps.

Maximum Design Pressures: -45 psf. (See General Limitation #7)

GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance; refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer.
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each side lap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq.

Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.

5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. Insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener value in conjunction with the maximum design value listed within a specific system. Should the fastener be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117 and/or RAS 137. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform to Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 61G20-3 of the Florida Administrative Code.

END OF THIS ACCEPTANCE

