



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)  
BOARD AND CODE ADMINISTRATION DIVISION

MIAMI-DADE COUNTY  
PRODUCT CONTROL SECTION  
11805 SW 26 Street, Room 208  
Miami, Florida 33175-2474  
T (786) 315-2590 F (786) 315-2599  
[www.miamidade.gov/](http://www.miamidade.gov/)

**NOTICE OF ACCEPTANCE (NOA)**

**NordBitumi dba Matco SRL**  
**Via Campagnola, 8**  
**37060, Sona-VR**  
**ITALY**

**SCOPE:**

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

**DESCRIPTION: Nord Bitumi SBS Self-Adhered Modified Bitumen Roof Systems over Concrete Decks**

**LABELING:** Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

**RENEWAL** of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

**TERMINATION** of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

**ADVERTISEMENT:** The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

**INSPECTION:** A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA renews NOA# 16-0113.02 and consists of pages 1 through 6.  
The submitted documentation was reviewed by Alex Tigera.



**NOA No: 21-0602.01**  
**Expiration Date: 05/26/26**  
**Approval Date: 06/24/21**  
**Page 1 of 6**

**ROOFING SYSTEM APPROVAL**

**Category:** Roofing  
**Sub-Category:** Modified Bitumen  
**Material:** SBS  
**Deck Type:** Concrete  
**Maximum Design Pressure:** -340 psf

**TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:**

**TABLE 1.**

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
Nordshield SA Base	39- <sup>3</sup> / <sub>8</sub> " x 65'7" (1m x 20m)	ASTM D 4601	Self-adhering SBS modified bitumen waterproofing membrane.
Nordshield SA Cap	39- <sup>3</sup> / <sub>8</sub> " x 32'10" (1m x 10m)	ASTM D 6164	Self-adhering SBS modified bitumen waterproofing membrane.

**APPROVED INSULATIONS:**

**TABLE 2**

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
ACFoam-II	Polyisocyanurate board faced with glass fiber reinforced cellulosic felts	Atlas Roofing Corporaton
Hunter H-Shield	Polyisocyanurate board faced with glass fiber reinforced cellulosic felts	Hunter Panels LLC
SECUROCK Gypsum-Fiber Roof Board	Gypsum board	United States Gypsum Corporation

**APPROVED FASTENERS:**

**TABLE 3**

<u>Fastener Number</u>	<u>Product Name</u>	<u>Product Description</u>	<u>Dimensions</u>	<u>Manufacturer (With Current NOA)</u>
1.	OMG Heavy Duty	Truss head, self-drilling, pinch point, high thread fastener for use in wood, steel, or concrete decks	#14 x 16" max. length; #3 phillips head	OMG, Inc.
2.	3 in. Round Metal Plate	Round galvalume steel stress plate for use with OMG fasteners	3" round	OMG, Inc.



**EVIDENCE SUBMITTED:**

<u>Test Agency</u>	<u>Test Identifier</u>	<u>Description</u>	<u>Date</u>
PRI Construction Material Technology	MTCO-010-02-01	TAS 114	08/03/15
	MTCO-002-02-01	ASTM D 6164	04/14/14
	MTCO-003-02-01	ASTM D 4601	03/31/14
	MTCO-008-02-01	TAS 117(B)	06/23/15
	MTCO-011-02-01	TAS 114	10/12/15
	MTCO-009-02-01	TAS 114	06/15/15



## APPROVED ASSEMBLIES

**Membrane Type:** SBS  
**Deck Type 3I:** Concrete Deck, Insulated  
**Deck Description:** Minimum 2500 psi structural concrete  
**System Type C(1):** All layers of insulation is mechanically attached. Membrane is subsequently fully adhered.

All General and System limitations apply.

One or more layers of any of the following insulations:

<u>Base Insulation Layer (Optional)</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft<sup>2</sup></u>
Atlas ACFoam-II, Hunter H-Shield Minimum 1/2" thick	N/A	N/A

**Note:** All layers shall be simultaneously fastened; see top layer below for fasteners and density. Insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

<u>Top Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft<sup>2</sup></u>
SECUROCK Gypsum-Fiber Roof Board Minimum 0.25" thick	1 with 2	1 : 1.6 ft <sup>2</sup>

**Note:** Base layer shall be mechanically attached with fasteners and density described. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).

**Base Sheet:** One or more plies of Nordshield SA Base, self-adhered with 4" wide side laps.  
**Membrane:** One ply of Nordshield SA Cap, self-adhered with 4" wide side laps.  
**Maximum Design Pressure:** - 52.5 psf (See General Limitation #7).



**Membrane Type:** SBS  
**Deck Type 3:** Concrete Deck  
**Deck Description:** Minimum 2500 psi structural concrete  
**System Type F(1):** Base sheet fully adhered

**All General and System limitations apply.**

**Note: Concrete deck shall be primed with ASTM D 41 asphalt primer and allowed to dry prior to application of anchor sheet.**

**Base Sheet:** One or more plies of Nordshield SA Base, self-adhered with 4" wide side laps.

**Membrane:** One ply of Nordshield SA Cap, self-adhered with 4" wide side laps.

**Maximum Design Pressure:** - 340 psf (See General Limitation #9).



**NOA No: 21-0602.01**  
**Expiration Date: 05/26/26**  
**Approval Date: 06/24/21**  
**Page 5 of 6**

## CONCRETE DECK SYSTEM LIMITATIONS:

1. If mechanical attachment to the structural deck through the lightweight insulating concrete is proposed, a field withdrawal resistance testing shall be performed to determine equivalent or enhanced fastener patterns and density. All testing and fastening design shall be in compliance with Testing Application Standard TAS 105 and Roofing Application Standard RAS 117; calculations shall be signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant.

## GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance, refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each sidelap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq. **Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**
5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform with Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 61G20-3 of the Florida Administrative Code.

**END OF THIS ACCEPTANCE**



NOA No: 21-0602.01  
Expiration Date: 05/26/26  
Approval Date: 06/24/21  
Page 6 of 6