



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)  
BOARD AND CODE ADMINISTRATION DIVISION

## NOTICE OF ACCEPTANCE (NOA)

**MIAMI-DADE COUNTY  
PRODUCT CONTROL SECTION**

11805 SW 26 Street, Room 208  
Miami, Florida 33175-2474  
T (786) 315-2590 F (786) 315-2599  
[www.miamidade.gov/economy](http://www.miamidade.gov/economy)

**Tarco Specialty Products, Inc.**  
**One Information Way**  
**Suite 225**  
**Little Rock, AR 72202**

### SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

### DESCRIPTION: Tarco Self-Adhering Modified Bitumen Roofing Systems over Recover Decks.

**LABELING:** Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

**RENEWAL** of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

**TERMINATION** of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

**ADVERTISEMENT:** The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

**INSPECTION:** A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA revises NOA No. 20-0721.08 and consists of pages 1 through 7.

The submitted documentation was reviewed by Jorge L. Acebo.

11/14/24



**NOA No.: 24-0430.01**  
**Expiration Date: 11/08/25**  
**Approval Date: 11/14/24**  
**Page 1 of 7**

## ROOFING SYSTEM APPROVAL

<b><u>Category:</u></b>	Roofing
<b><u>Sub-Category:</u></b>	Modified Bitumen
<b><u>Material:</u></b>	SBS
<b><u>Deck Type:</u></b>	Recover
<b><u>Maximum Design Pressure:</u></b>	See specific system assembly

## TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<b><u>Product</u></b>	<b><u>Dimensions</u></b>	<b><u>Test Specification</u></b>	<b><u>Product Description</u></b>
LeakBarrier® EasyLay™	3' x 133'4" rolls	ASTM D 226 Type II	Mechanically attached, asphalt coated polyester base sheet.
LeakBarrier® EasyBase™	3' x 72' rolls	ASTM D 4601, Type I	Self-adhered, fiberglass reinforced, smooth surfaced SBS modified bitumen base ply membrane.
TOPSHIELD STORMGEAR™ SA BASE	3' x 72' rolls	ASTM D 4601, Type I	Self-adhered, fiberglass reinforced, smooth surfaced SBS modified bitumen base ply membrane.
LeakBarrier® EasyStick Plus™	3' x 36' rolls	ASTM D 6164, Type I	Self-adhered, polyester reinforced, granule surfaced SBS modified bitumen cap ply membrane.
TOPSHIELD STORMGEAR™ SA CAP	3' x 36' rolls	ASTM D 6164, Type I	Self-adhered, polyester reinforced, granule surfaced SBS modified bitumen cap ply membrane.

## APPROVED INSULATIONS:

TABLE 2

<b><u>Product Name</u></b>	<b><u>Product Description</u></b>	<b><u>Manufacturer</u></b> <b><u>(With Current NOA)</u></b>
SECUROCK Gypsum-Fiber Roof Board	Rigid, gypsum-based board stock	USG Corporation



NOA No.: 24-0430.01  
Expiration Date: 11/08/25  
Approval Date: 11/14/24  
Page 2 of 7

**APPROVED FASTENERS:****TABLE 3**

<b><u>Fastener Number</u></b>	<b><u>Product Name</u></b>	<b><u>Product Description</u></b>	<b><u>Dimensions</u></b>	<b><u>Manufacturer (With Current NOA)</u></b>
1.	#12 Standard Roofgrip, OMG Heavy Duty	Roofing and insulation fasteners, with #3 Phillips head.	Various	OMG, Inc.
2.	OMG 3" Galvalume Steel Plate	Galvalume steel stress plates.	3" round	OMG, Inc.
3.	Trufast #12 DP Fastener	Insulation fastener for wood, steel and concrete		Altenloh, Brinck & Co. U.S., Inc.
4.	Trufast #14 HD Fastener	Insulation fastener for wood, steel and concrete		Altenloh, Brinck & Co. U.S., Inc.
5.	Trufast 3" Metal Insulation Plate	Galvalume steel stress plate	3" round	Altenloh, Brinck & Co. U.S., Inc.

**EVIDENCE SUBMITTED:**

<b><u>Test Agency</u></b>	<b><u>Test Identifier</u></b>	<b><u>Test Name/Report</u></b>	<b><u>Date</u></b>
Southwest Research Institute	10.16924.01.220a	ASTM E108	11/02/12
	10.16924.01.220b	ASTM E108	11/02/12
Trinity   ERD	T6460.06.07-R2	TAS 114(J)	06/26/07
	T39040.11.11-R1	TAS 114 (H)	11/21/11
	TAR-SC13965.02.17-R1	ASTM D226	02/27/17
	TAR-SC16545.11.17	ASTM D4601	11/01/17
NEMO ETC, LLC.	4-TAR-18-002.04.18	ASTM D6164 / TAS 110	04/16/18



## APPROVED ASSEMBLIES

**Membrane Type:** SBS

**Deck Type 7I:** Recover, Insulated

**Deck Description:**  $1\frac{9}{32}$ " or greater plywood or wood plank attached with 8d ring shank nails spaced 6" o.c. at wood joists spaced maximum 24" o.c. \*The deck shall record a Minimum Characteristic Resistance Force (MCRF) of 105 lbf. when tested with fasteners, listed in this assembly, installed through to the deck in accordance with TAS 105.

**System Type C:** All layers of insulation are mechanically attached to roof deck.

**All General and System Limitations apply.**

One or more layers of the following:

<u>Insulation Layer</u>	<u>Insulation Fasteners</u> <u>(Table 3)</u>	<u>Fastener</u> <u>Density/ft<sup>2</sup></u>
SECUROCK Gypsum-Fiber Roof Board Minimum 3/8" thick	1, 2, 3, 4, 5	1:1 ft <sup>2</sup>

**Note:** Base layers of insulation shall be mechanically attached using the fastener density listed. The insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

**Base Sheet:** One ply of LeakBarrier® EasyBase™ or TOPSHIELD STORMGEAR™ SA MOD BASE self-adhered.

**Ply Sheet:** (Optional) One ply of LeakBarrier® EasyBase™ or TOPSHIELD STORMGEAR™ SA MOD BASE self-adhered.

**Cap Sheet:** One ply of LeakBarrier® EasyStick Plus™ or TOPSHIELD STORMGEAR™ SA CAP self-adhered.

**Surfacing:** (Optional) Install one of the following to obtain required fire classification. Any coating, listed below, used as a surfacing, must be listed within a current NOA.

1. Gravel or slag at 400 lbs./sq or 300 lbs./sq, respectively, in a flood coat of approved asphalt at 60 lbs./sq.
2. Karnak 97 Fibrated Aluminum Asphalt Roof Coating or Asbestos Free Aluminum Roof Coating at 1½ gal./sq.

**Maximum Design Pressure:**

-52.5 psf (See General Limitation #7.)



NOA No.: 24-0430.01  
Expiration Date: 11/08/25  
Approval Date: 11/14/24  
Page 4 of 7

**Membrane Type:** SBS

**Deck Type 7I:** Recover, Insulated

**Deck Description:** <sup>19</sup>/<sub>32</sub>" or greater plywood or wood plank attached with 8d ring shank nails spaced 6" o.c. at wood joists spaced maximum 24" o.c. \*The deck shall record a Minimum Characteristic Resistance Force (MCRF) of 89 lbf. when tested with fasteners, listed in this assembly, installed through to the deck in accordance with TAS 105.

**System Type D:** All layers of insulation and base sheet simultaneously attached.

**All General and System Limitations apply.**

One or more layers of the following:

<u>Insulation Layer</u>	<u>Insulation Fasteners</u> (Table 3)	<u>Fastener</u> <u>Density/ft<sup>2</sup></u>
SECUROCK Gypsum-Fiber Roof Board Minimum 3/8" thick	N/A	N/A

**Note:** Base layers of insulation shall be mechanically attached using the fastener density listed. The insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

**Base Sheet:** One or more plies of LeakBarrier® EasyLay™, mechanically attached 10" o.c. in the min. 4" lap and 10" o.c. in two, equally spaced, staggered center rows with #12 Standard Roofgrip or OMG Heavy Duty fasteners with OMG 3" Galvalume Steel Plates.

**Ply Sheet:** One ply of LeakBarrier® EasyBase™ or TOPSHIELD STORMGEAR™ SA MOD BASE self-adhered.

**Cap Sheet:** One ply of LeakBarrier® EasyStick Plus™ or TOPSHIELD STORMGEAR™ SA CAP self-adhered.

**Surfacing:** (Optional) Install one of the following to obtain required fire classification. Any coating, listed below, used as a surfacing, must be listed within a current NOA.

1. Gravel or slag at 400 lbs./sq or 300 lbs./sq, respectively, in a flood coat of approved asphalt at 60 lbs./sq.
2. Karnak 97 Fibrated Aluminum Asphalt Roof Coating or Asbestos Free Aluminum Roof Coating at 1½ gal./sq.

**Maximum Design Pressure:** -60 psf (See General Limitation #7.)



NOA No.: 24-0430.01  
 Expiration Date: 11/08/25  
 Approval Date: 11/14/24  
 Page 5 of 7

**Membrane Type:** SBS

**Deck Type 7:** Recover, Non-Insulated

**Deck Description:** <sup>19</sup>/<sub>32</sub>" or greater plywood or wood plank attached with 8d ring shank nails spaced 6" o.c. at wood joists spaced maximum 24" o.c. \*The deck shall record a Minimum Characteristic Resistance Force (MCRF) of 23 lbf. when tested with fasteners, listed in this assembly, installed through to the deck in accordance with TAS 105.

**System Type E:** Base sheet mechanically fastened.

**All General and System Limitations apply.**

**Base Sheet:** One ply of LeakBarrier® EasyLay™ fastened to the deck as described below:

**Fastening #1:** Attach base sheet using 12 ga. annular ring shank nails with min. 32 ga., 1-5/8" diameter tin-caps spaced 7" o.c. in the 4" lap and 7" o.c. in three, equally spaced, staggered center rows.

**Fastening #2:** Attach base sheet using #12 Standard Roofgrip or OMG Heavy Duty fasteners with OMG 3" Galvalume Steel Plates or Trufast #12 DP or Trufast #14 HD Fasteners with Trufast 3" Metal Insulation Plates spaced 10" o.c. in the min. 4" lap and 10" o.c. in two, equally spaced, staggered center rows.

**Ply Sheet:** One ply of LeakBarrier® EasyBase™ or TOPSHIELD STORMGEAR™ SA MOD BASE self-adhered.

**Cap Sheet:** One ply of LeakBarrier® EasyStick Plus™ or TOPSHIELD STORMGEAR™ SA CAP self-adhered.

**Surfacing:** (Optional) Install one of the following to obtain required fire classification. Any coating, listed below, used as a surfacing, must be listed within a current NOA.

1. Gravel or slag at 400 lbs./sq or 300 lbs./sq, respectively, in a flood coat of approved asphalt at 60 lbs./sq.
2. Karnak 97 Fibrated Aluminum Asphalt Roof Coating or Asbestos Free Aluminum Roof Coating at 1½ gal./sq.

**Maximum Design Pressure:** -60 psf (See General Limitation #7.)



## RECOVER SYSTEM LIMITATIONS:

1. All System Limitations and General Limitations shall apply. See specific deck type Noticed of Acceptance for deck type System Limitations.
2. All assemblies listed herein shall be installed in compliance with the applicable sections of FBC 1521. Uplift performance of assemblies bonded to existing roofing system shall be verified per 1521.10. Uplift performance of assemblies mechanically attached through existing roofing system shall be verified per 1521.11.

## GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance; refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each side lap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq.  
**Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**
5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform to Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 61G20-3 of the Florida Administrative Code.

**END OF THIS ACCEPTANCE**



NOA No.: 24-0430.01  
Expiration Date: 11/08/25  
Approval Date: 11/14/24  
Page 7 of 7