



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)
BOARD AND CODE ADMINISTRATION DIVISION

**MIAMI-DADE COUNTY
PRODUCT CONTROL SECTION**

11805 SW 26 Street, Room 208
Miami, Florida 33175-2474
T (786) 315-2590 F (786) 315-2599

www.miamidade.gov/economy

NOTICE OF ACCEPTANCE (NOA)

Sika Corporation
201 Polito Avenue
Lyndhurst, New Jersey 07071

SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER -Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

DESCRIPTION: Sikalastic Roofing & Waterproofing Systems

LABELING: Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

RENEWAL of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

TERMINATION of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

ADVERTISEMENT: The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

INSPECTION: A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA renews and revises NOA# 23-1219.07 and consists of pages 1 through 33.
The submitted documentation was reviewed by Alex Tigera.

07/16/26



NOA No.: 25-0623.09
Expiration Date: 07/09/31
Approval Date: 07/16/26
Page 1 of 33

ROOFING SYSTEM APPROVAL

Category: Roofing
Sub-Category: Waterproofing
Material: Polyurethane
Deck Type: Concrete
Maximum Design Pressure: -502.5 psf

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
Sika Fleece 120, 140 & 170	48' x 300' Roll	Proprietary	A non-woven needle-punched polyester fleece which is capable of stretching within the membrane to accommodate a high degree of thermal and structural movement.
Sikalastic 621 TC	5 gal. pails	ASTM D 6083	A single component, moisture triggered; aliphatic polyurethane elastomeric coating. Used as a UV stable top coat which is available in a variety of colors.
Sikalastic 624 WP	5 gal pails	ASTM C 836	Sikalastic 624 WP is a single component moisture triggered alkaline resistant, elastomeric polyurethane liquid applied waterproofing membrane
Sikalastic 644 Lo-VOC	5 gal pails	ASTM C 836	A single component, moisture triggered, alkaline resistant, elastomeric polyurethane liquid applied waterproofing membrane
Sikalastic 641 Lo-VOC	5 gal pails	ASTM C 836	A cold applied, aliphatic, single component, moisture triggered, polyurethane resin.
Reemat Premium	49" x 295' Roll	Proprietary	A randomly oriented glass fiber reinforcement scrim which is capable of stretching within the membrane to accommodate a high degree of thermal and structural movement.
Sikalastic GDC Primer	4 gal	Proprietary	Two-component epoxy primer for green and damp cementitious substrates.
Sikalastic DTE Primer	1 gal	Proprietary	Two-component epoxy primer for damp cementitious substrates.
Sika Bonding Primer	1 gal	Proprietary	Two-component water based epoxy primer.
Sikalastic EP Primer/Sealer	1 or 4 gal	Proprietary	-Two-component solvent based epoxy primer
Sika Concrete Primer Lo-VOC	5 gal	Proprietary	Cold applied, single-component, low-odor moisture-curing polyurethane primer.



NOA No.: 25-0623.09
 Expiration Date: 07/09/31
 Approval Date: 07/16/26
 Page 2 of 33

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:**TABLE 1**

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
Sika Drainage Mat 420	4' x 50'	Proprietary	Prefabricated polypropylene and non-woven filter fabric drainage mat for soil or stone type overburden.
Sika Drainage Mat 720	4' x 50'	Proprietary	Prefabricated polypropylene and woven filter fabric drainage mat for cementitious type overburden.
Sika Drainage Mat 1000	4' x 50'	Proprietary	Prefabricated high density polyethylene geonet drainage core between two layers of nonwoven polypropylene filter fabrics for cementitious type overburden with heavy vehicle traffic.
Sika Drainage Mat GRS	4' x 50'	Proprietary	Prefabricated polypropylene and non-woven filter fabric drainage mat with a root-resistant top side.

APPROVED INSULATIONS:**TABLE 2**

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
Insulfoam EPS	Expanded Polystyrene (Type IX)	Insulfoam – a division of Carlisle Construction Materials LLC
R-TECH	Expanded Polystyrene (Type IX)	Insulfoam – a division of Carlisle Construction Materials LLC
Kingspan GreenGuard Insulation Board	Extruded Polystyrene	Kingspan Insulation, LLC
STYROFOAM ROOFMATE	Extruded Polystyrene (Type VI)	DuPont de Nemours, Inc.
STYROFOAM PLAZAMATE	Extruded Polystyrene (Type VII)	DuPont de Nemours, Inc.
STYROFOAM HIGHLOAD 60	Extruded Polystyrene (Type VII)	DuPont de Nemours, Inc.



TRADE NAMES OF PRODUCTS MANUFACTURED BY OTHERS

TABLE 3

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>	<u>Manufacturer</u>
Silica Sand	Pre-packaged bags	N/A	Clean, rounded, oven dried quartz sand with a minimum size gradation of 16-30 mesh for vehicular traffic and 20-40 mesh for pedestrian traffic, and a minimum hardness of 6.5 per the Moh's scale. It should be free of metallic or other impurities. The seeding of the aggregate shall be with an even, light broadcast short of or just to refusal. Any loose aggregate must be removed prior to recoating. Back roll aggregate where indicated.	Generic
MAPEI Ceramic Tile Mortar	50 lb. bag	ANSI A118.4	Polymer enriched thin set mortar	Mapei
Versabond Fortified Thin Set Mortar	25 & 50 lb. bag	ANSI A118.4	Polymer modified thin set mortar	Custom Building Products
Laticrete 254 Platinum Mortar	50 lb. bag	ANSI A118.4	Polymer fortified thin set mortar	Laticrete International, Inc.
SikaTile-475 LHT	50 lb. bag		One step polymer modified Portland cement setting adhesive for installing extra large format porcelain, ceramic tile and natural stone	Sika Corp.
Tile	12" x 12" x ¼"	ANSI A137.1	Porcelain deck walking tiles	Generic
HANOVER PREST BRICK TRADITIONAL	12" x 12" x 2"		Concrete Paver	Hanover Architectural Products
HANOVER PREST BRICK TRADITIONAL	8" x 4" x 2"		Concrete Paver	Hanover Architectural Products
Structural Concrete	2500 psi minimum		Concrete over burden	Generic
3M Scotch-Weld™ Pedestal Adhesive	Cartridges		Pedestal Adhesive	3M
Terra Stand Screw Top Pedestal with Lok-Down	24" x 24" x 2"		Pedestal and Paver System	Wausau Tile



EVIDENCE SUBMITTED:

<u>Test Agency</u>	<u>Test Identifier</u>	<u>Test Specification</u>	<u>Date</u>
PRI Construction Materials Technologies	LPI-045-02-01	ASTM D 7311	12/04/12
	LPI-046-02-01	ASTM C 297	10/20/14
	LPI-049-02-01	TAS 114 D	10/06/14
	LPI-049-02-02	TAS 114 D	10/06/14
	LPI-052-02-01	ASTM C 836	12/18/14
	LPI-062-02-01	TAS 114 D	02/18/15
	LPI-070-02-01.1	ASTM D 4541	08/28/17
	LPI-078-02-01.1	ASTM D 562/ASTM D 1475/ASTM D 1644/ ASTM D 96	08/29/17
	577T0023	ASTM D 562/ASTM D 1475/ASTM D 1644/ ASTM D 4541	06/09/21
	577T0024	ASTM D 4541	11/15/19
	577T0044	ASTM D 4541	02/22/21
	577T0050	TAS 114 D	05/17/21
	577T0051	ASTM D 6083	05/17/21
	577T0055	ASTM D 4541	05/17/21
	577T0056	ASTM D 6083	08/17/21
	577T0060	ASTM C 836	06/28/21
	577T0099	ASTM D 1475 / ASTM 2196 ASTM D 638 / ASTM C 794	04/28/22
Atlantic & Caribbean Roof Consulting, LLC	21-013	TAS 114 D	06/09/21
Intertek	101892419MID-001a	ASTM E 108	11/19/14
SGS Tech Services	24-0971	ASTM D7311	01/15/25
	24-0972	ASTM C836	02/03/25
FM Approvals	3054266	4470	06/06/16
	2049736	4470	06/02/24
	3063191	4470	12/06/17
NEMO	4a-SIKAC-22-LSWUS-	ANSI/FM 4474(D)	02/14/23
	01.A.R1	TAS 114(J) /UL 1897	



APPROVED APPLICATIONS:

Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(1):	Sikalastic 624 WP System with Tiles

Substrate Preparation: Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer.

All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).

Primer: Choose one of the following primers required:

1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.

Liquid applied systems: In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-624 WP max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 53 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into the wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-624 WP at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 50 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once base coat is properly cured, apply one coat of Sikalastic 624 WP max rate of 40 ft²/gal. (40 wet mils) *Coating system shall have a minimum total film thickness of 60 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 32 ft²/gal. (min. 50 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 45 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 60 mils dry.

System Option III (25-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply two coats of Sikalastic-624 WP max rate of 53 ft²/gal. (min. 30 wet mils each). Allow each coat to properly cure before applying the next coat. *Coating system shall have a minimum Total Film Thickness of 75 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 24 ft²/gal. (min. 65 wet mils).
- Reinforcement:** Sika Fleece 170 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 40 ft²/gal. (min. 40 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 75 mils dry.
- Sand-Coat** Once top coat is cured apply an additional coat of Sikalastic 624 WP applied at a min. 15 mils wet (100 ft²/gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat to rejection. Remove excess sand prior to topping.
- Integrity Test:** Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required.
- Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
- Inspection:** Contractor and a representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
- Topping/
Overburden:** Nominal 12" x 12" x 1/4" porcelain tiles complying with ANSI A137.1 attached with one of the following:
1. Laticrete 254 Platinum thin-set mortar applied with 1/4" x 3/8" x 1/4" notched trowel.
 2. Versabond Fortified Thin-Set Mortar applied with 1/4" x 3/8" x 1/4" notched trowel.
 3. MAPEI Ceramic Tile Mortar applied with 1/4" x 3/8" x 1/4" notched trowel.
 4. SikaTile-475 LHT
- Maximum Design Pressure:** -495 psf (See General Limitation #9)

Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(2):	Sikalastic 644 Lo-VOC System with Tiles
Substrate Preparation:	Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Liquid applied systems:	In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one coat of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness 56 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-644 Lo-VOC at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 56 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one coat of Sikalastic 644 Lo-VOC at a max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 32 ft²/gal. (min. 50 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-644 Lo-VOC at a max. rate of 45 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.



System Option III (25-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply two coats of Sikalastic-644 LO-VOC max rate of 35 ft²/gal. (min. 45 wet mils each). Allow each coat to properly cure before applying the next coat. *Coating system shall have a minimum Total Film Thickness of 76 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 27 ft²/gal. (min. 60 wet mils).
- Reinforcement:** Sika Fleece 170 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-644 Lo-VOC at a max. rate of 45 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 76 mils dry.
- Sand-Coat** Once top coat is cured apply an additional coat of Sikalastic-644 Lo-VOC should be applied at a min. 15 mils wet (100 ft²/gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat to rejection. Remove excess sand prior to topping.
- Integrity Test:** Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required.
- Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
- Inspection:** Contractor and representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
- Topping/
Overburden:** Nominal 12" x 12" x 1/4" porcelain tiles complying with ANSI A137.1 attached with one of the following:
1. Laticrete 254 Platinum thin-set mortar applied with 1/4" x 3/8" x 1/4" notched trowel.
 2. SikaTile-475 LHT thin set mortar with 1/4" x 3/8" x 1/4" notched trowel.
 3. MAPEI Ceramic Tile Mortar applied with 1/4" x 3/8" x 1/4" notched trowel.
 4. SikaTile-475 LHT
- Maximum Design Pressure:** -495 psf (See General Limitation #9)

Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(3):	Sikalastic 624 WP System, Dual Slab
Substrate Preparation:	Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 3-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 24 hours of primer application. 4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Liquid applied systems:	In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP should be applied at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat** Once the base coat is properly cured, apply one or more coats of Sikalastic-624 WP at a max rate of 53 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 53 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP should be applied at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into the wet base coat.
- Top-Coat** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-624 WP at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 50 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top Coat:** Once base coat is properly cured, apply one coat of Sikalastic 624 WP max rate of 40 ft²/gal. (40 wet mils) *Coating system shall have a minimum total film thickness of 60 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 32 ft²/gal. (min. 50 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 45 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 60 mils dry.

System Option III (25-year system)

Base Coat:	Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft ² /gal. (min. 45 wet mils).
Reinforcement:	Sika Reemat Premium back rolled into the wet base coat.
Top Coat:	Once the base coat is properly cured, apply two coats of Sikalastic-624 WP max rate of 53 ft ² /gal. (min. 30 wet mils each). Allow each coat to properly cure before applying the next coat. *Coating system shall have a minimum Total Film Thickness of 75 mils dry. OR
Base Coat:	Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 24 ft ² /gal. (min. 67 wet mils).
Reinforcement:	Sika Fleece 170 back rolled into wet base coat.
Top Coat:	Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 40 ft ² /gal. (min. 40 wet mils). *Coating system shall have a minimum Total Film Thickness of min. 75 mils dry.
Sand-Coat	Once top coat is cured apply an additional coat of Sikalastic 624 WP should be applied at a min. 15 mils wet (100 ft ² /gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat. Remove excess sand prior to topping.
Integrity Test:	Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required. Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration
Inspection:	Contractor and representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
Protection Course (Optional):	Any insulation listed in Table 2 must be loose laid prior to pouring the concrete topping slab. Refer to manufacturer's instructions for additional installation requirements. And/Or Sika Drainage Mat 720 or 1000 must be loose laid prior to pouring the concrete topping slab. Refer to manufacturer's instructions for additional installation requirements.
Topping/Overburden:	Structural Concrete Topping, minimum 2500 psi, with a minimum 2" thickness in accordance with applicable building code.
Maximum Design Pressure:	N/A



Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(4):	Sikalastic System – Sikalastic 621 TC or Sikalastic 641 Lo-VOC
Substrate Preparation:	Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 3-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sikalastic DTE Primer with a flat squeegee or a roller at approximately 200 sq. ft. /gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-200 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 4. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Base Coat:	Sikalastic 621 TC should be applied at a min. 45 wet mils (max. 35ft ² /gal.) using a roller or notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.
Reinforcement:	Sika Reemat Premium is embedded into the wet base coat.
Top-Coat	Once the base coat is properly cured apply Sikalastic 621 TC should be applied at a min. of 30 mils wet (53 ft²/gal.) using a roller or notched squeegee and back roll using a phenolic resin core roller. *Coating system shall have a minimum Total Film Thickness of 61 mils dry. OR

Base Coat:	Once the primer is properly cured, apply Sikalastic-621 TC at a max. rate of 32 ft ² /gal. (min. 50 wet mils).
Reinforcement:	Sika Fleece 140 is embedded into the wet base coat.
Top-Coat	Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-621 TC at a max. rate of 45 ft ² /gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.
Optional Non-Skid Coat:	Once top coat is cured apply and additional coat of Sikalastic 621 TC should be applied at a min.15 mils wet (max. 100 ft ² /gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply dry silica sand evenly distributed broadcast at a rate of 2.75 lbs/100 ft ² into the wet nonskid coat and back roll to embed sand. Allow coating to cure a minimum of 16 hours at 70°F and 50% RH or until tack free between coats, and a minimum of 72 hours before opening to pedestrian traffic. OR
Base Coat:	Sikalastic 641 Lo-VOC should be applied at a min. 50 wet mils (max. 32ft ² /gal.) using a roller or notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints..
Reinforcement:	Sika Reemat Premium is embedded into the wet base coat.
Top-Coat	Once base coat is properly cured apply Sikalastic 641 Lo-VOC at a min. of 30 mils wet (53 ft ² /gal.) using a roller or notched squeegee and back roll using a phenolic resin core roller. *Coating system shall have a minimum Total Film Thickness of 71 mils dry. OR
Base Coat:	Once the primer is properly cured, apply Sikalastic-641 Lo-VOC at a max. rate of 32 ft ² /gal. (min. 50 wet mils)...
Reinforcement:	Sika Fleece 140 is embedded into the wet base coat.
Top-Coat	Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-641 Lo-VOC at a max. rate of 53 ft ² /gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of 71 mils dry.
Optional Non-Skid Coat:	Once top coat is cured apply an additional coat of Sikalastic 641 Lo-VOC at a min.15 mils wet (max. 100 ft ² /gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply dry silica sand evenly distributed broadcast at a rate of 2.75 lbs/100 ft ² into the wet nonskid coat and back roll to embed sand. Allow coating to cure a minimum of 16 hours at 70°F and 50% RH or until tack free between coats, and a minimum of 72 hours before opening to pedestrian traffic.

Integrity Test:	Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required. Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration
Inspection:	Contractor and a representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
Maximum Design Pressure:	-502.5 psf (See General Limitation #9)

Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(5):	Sikalastic 624 WP System, Planters
Substrate Preparation:	Surface must be clean and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 24 hours of primer application. 4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Liquid applied systems:	In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

Base Coat: Once the primer is properly cured, apply Sikalastic 624 WP should be applied at a max. rate of 35 ft²/gal. (min. 45 wet mils).

Reinforcement: Sika Reemat Premium back rolled into the wet base coat.

Top-Coat Once the base coat is properly cured, apply one coat of Sikalastic-624 WP at a max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 53 mils dry.

OR

Base Coat: Once the primer is properly cured, apply Sikalastic 624 WP should be applied at a max. rate of 35 ft²/gal. (min. 45 wet mils).

Reinforcement: Sika Fleece 120 back rolled into the wet base coat.

Top-Coat Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 50 mils dry.

System Option II (20-year system)

Base Coat: Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).

Reinforcement: Sika Reemat Premium back rolled into wet base coat.

Top Coat: Once the base coat is properly cured, apply one coat of Sikalastic-624 WP at a max rate of 40 ft²/gal. (min. 40 wet mils). *Coating system shall have a minimum Total Film Thickness of. 60 mils dry.

OR

Base Coat: Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 32 ft²/gal. (min. 50 wet mils).

Reinforcement: Sika Fleece 140 back rolled into wet base coat.

Top Coat: Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 45 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 60 mils dry.

System Option III (25-year system)

Base Coat:	Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft ² /gal. (min. 45 wet mils).
Reinforcement:	Sika Reemat Premium back rolled into wet base coat.
Top Coat:	Once the base coat is properly cured, apply two coats of Sikalastic-624 WP at a max rate of 53 ft ² /gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of 75 mils dry. OR
Base Coat:	Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 24 ft ² /gal. (min. 65 wet mils).
Reinforcement:	Sika Fleece 170 back rolled into wet base coat.
Top Coat:	Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 40 ft ² /gal. (min. 40 wet mils). *Coating system shall have a minimum Total Film Thickness of min. 75 mils dry.
Sand Coat: (Optional)	Sikalastic 624 WP should be applied at a min. 15 mils wet (max. 100 ft ² /gal). Apply a full dry silica sand broadcast evenly distributed at the rate of 50 lbs./100 ft ² - into the wet coat. Remove excess sand prior to topping.
Integrity Test:	Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required. Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
Inspection:	Contractor and a representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
Drainage Layer:	Sika Drainage Mat 420 or GRS loose laid over top coat.
Surfacing:	Backfill the planter with minimum 24" of medium soil.
Maximum Design Pressure:	-502.5 psf (See General Limitation #9)



Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(6):	Sikalastic 644 Lo-VOC System, Planters
Substrate Preparation:	Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 24 hours of primer application. 4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Liquid applied systems:	In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 56 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 56 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 60 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.



System Option III (25-yr System)

Base Coat:	Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft ² /gal. (min. 45 wet mils).
Reinforcement:	Sika Reemat Premium back rolled into the wet base coat.
Top-Coat:	Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft ² /gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 76 mils dry. OR
Base Coat:	Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 27 ft ² /gal. (min. 60 wet mils).
Reinforcement:	Sika Fleece 170 back rolled into wet base coat.
Top-Coat:	Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-644 Lo-VOC at a max. rate of 45 ft ² /gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of 76 mils dry.
Sand-Coat: (Optional)	Once the top coat is cured apply and additional coat of Sikalastic-644 Lo-VOC at a min. 15 mils wet Sikalastic-644 Lo-VOC should be applied at a min. 15 mils wet (100 ft ² /gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat to rejection. Remove excess sand prior to topping.
Integrity Test:	Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required. Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
Inspection:	Contractor and representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
Drainage Layer:	Sika Drainage Mat 420 or GRS loose laid over top coat.
Surfacing:	Backfill the planter with minimum 24" of medium soil.
Maximum Design Pressure:	-502.5 psf (See General Limitation #9)



Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(7):	Sikalastic 644 Lo-VOC System with Dual Slab
Substrate Preparation:	Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 24 hours of primer application. 4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Liquid applied systems:	In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 56 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into the wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-644 Lo-VOC at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 56 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one coat of Sikalastic-644 Lo-VOC max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 32 ft²/gal. (min. 50 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-644 Lo-VOC at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.



System Option III (25-year system)

Base Coat:	Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft ² /gal. (min. 45 wet mils).
Reinforcement:	Sika Reemat Premium back rolled into wet base coat.
Top-Coat:	Once the base coat is properly cured, apply two coats of coats Sikalastic-644 Lo-VOC max rate of 64 ft ² /gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 76 mils dry. OR
Base Coat:	Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 27 ft ² /gal. (min. 60 wet mils).
Reinforcement:	Sika Fleece 170 back rolled into wet base coat.
Top-Coat:	Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-644 Lo-VOC at a max. rate of 45 ft ² /gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 76 mils dry.
Sand-Coat: (Optional)	Once top coat is cured apply an additional coat of Sikalastic-644 Lo-VOC at a min. 15 mils wet (100 ft ² /gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat to rejection. Remove excess sand prior to topping.
Integrity Test:	Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required. Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
Inspection:	Contractor and representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
Protection Course (Optional):	Any insulation listed in Table 2 must be loose laid prior to pouring the concrete topping slab. Refer to manufacturer's instructions for additional installation requirements. And/Or Sika Drainage Mat 720 or 1000 must be loose laid prior to pouring the concrete topping slab. Refer to manufacturer's instructions for additional installation requirements.
Topping/ Overburden:	Structual Concrete Topping, minimum 2500 psi, with a minimum 2" thickness in accordance with applicable building code.
Maximum Design Pressure:	N/A



Deck Type 1	Concrete Decks
Deck Description:	Min. 2500 psi
System Type F(8):	Sikalastic 644 Lo-VOC System with Pavers
Substrate Preparation:	Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer. All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).
Primer:	Choose one of the following primers required: 1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application. 3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 24 hours of primer application. 4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
Liquid applied systems:	In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 56 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into the wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-644 Lo-VOC at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 56 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.

OR

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 32 ft²/gal. (min. 50 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-644 Lo-VOC at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.



System Option III (25-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-644 Lo-VOC max rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 76 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-644 Lo-VOC at a max. rate of 27 ft²/gal. (min. 60 wet mils).
- Reinforcement:** Sika Fleece 170 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-644 Lo-VOC at a max. rate of 45 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of 76 mils dry.
- Sand-Coat** Once top coat is cured apply an additional coat of Sikalastic-644 Lo-VOC should be applied at a min. 15 mils wet (100 ft²/gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat to rejection. Remove excess sand prior to topping.
- Integrity Test:** Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required.
- Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
- Inspection:** Contractor and a representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
- Topping/
Overburden:** Nominal 8" x 4" x 2" Hanover Prestbrick or Traditional Concrete Paver, attached with one SikaTile-475 LHT thin set mortar with 1/2" x 1/2" x 1/2" notched trowel.
- Maximum Design
Pressure:** -502.5 psf (See General Limitation #9)

Deck Type 1 Concrete Decks
Deck Description: Min. 2500 psi
System Type F(9): Sikalastic 624 WP System with Pavers

Substrate Preparation: Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes, and any other contaminants. All projections, rough spots, etc. should be addressed to achieve a level surface prior to the application. All concrete surfaces must be dry before applying primer with the exception of Sikalastic GDC Primer.

All concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 2-4 per ICRI guidelines).

Primer: Choose one of the following primers required:

1. Apply Sikalastic DTE Primer with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
2. Apply Sika Concrete Primer Lo-VOC with a flat squeegee or roller at approximately 200 ft²/gal and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.
3. Apply Sikalastic EP Primer/Sealer with a flat squeegee or roller at approximately 100-250 ft²/gal. and work well into the substrate to ensure adequate penetration and sealing and puddles are avoided. Allow primer to dry tack free. Base coat must be applied within 24 hours of primer application.
4. Apply Sikalastic GDC Primer at a rate of 95-112 ft²/gal. with a flat squeegee or roller and work well into the substrate to ensure adequate penetration and sealing. Primer should have a mirror-like finish when adequate application thickness is reached. Allow primer to dry tack free. Base coat must be applied within 72 hours of primer application.

Liquid applied systems: In all system options below, use a roller, notched squeegee or trowel and back roll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints.

System Option I (15-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-624 WP max rate of 53 ft²/gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 53 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Fleece 120 back rolled into the wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 64 ft²/gal. (min. 25 wet mils). *Coating system shall have a minimum Total Film Thickness of 50 mils dry.

System Option II (20-year system)

- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft²/gal. (min. 45 wet mils).
- Reinforcement:** Sika Reemat Premium back rolled into the wet base coat.
- Top-Coat:** Once the base coat is properly cured, apply one or more coats of Sikalastic-624 WP max rate of 40 ft²/gal. (min. 40 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 60 mils dry.
- OR
- Base Coat:** Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 32 ft²/gal. (min. 50 wet mils).
- Reinforcement:** Sika Fleece 140 back rolled into wet base coat.
- Top-Coat:** Immediately after placing and saturating the Reinforcement, apply one coat of Sikalastic-624 WP at a max. rate of 45 ft²/gal. (min. 35 wet mils). *Coating system shall have a minimum Total Film Thickness of 60 mils dry.

System Option III (25-year system)

Base Coat:	Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 35 ft ² /gal. (min. 45 wet mils).
Reinforcement:	Sika Reemat Premium back rolled into the wet base coat.
Top-Coat:	Once the base coat is properly cured, apply two coats of Sikalastic-624 WP at a max rate of 53 ft ² /gal. (min. 30 wet mils). *Coating system shall have a minimum Total Film Thickness of 74 mils dry. OR
Base Coat:	Once the primer is properly cured, apply Sikalastic-624 WP at a max. rate of 24 ft ² /gal. (min. 65 wet mils).
Reinforcement:	Sika Fleece 170 back rolled into wet base coat.
Top-Coat:	Immediately after placing and saturating the Reinforcement, apply a coat of Sikalastic-624 WP at a max. rate of 40 ft ² /gal. (min. 40 wet mils). *Coating system shall have a minimum Total Film Thickness of Min. 75 mils dry.
Sand-Coat:	Once top coat is cured apply an additional coat of Sikalastic 624 WP at a min 15 mils wet (100 ft ² /gal) using a roller or notched squeegee and back roll using a phenolic resin core roller. Apply silica sand evenly distributed at the rate of 50lbs/100sq.ft.- into the wet coat to rejection. Remove excess sand prior to topping.
Integrity Test:	Required, and shall be performed in accordance with ASTM D 5957 by an approved lab. Water may be maintained for a period longer than 24 hours if required. Verify that the structure can support the deadload weight of a watertight test before proceeding. The integrity of the cured membrane on a horizontal surface may be verified by damming the entire area and flooding with water to a minimum depth of 2" and allowing the water to stand for 24-48 hours. Visually inspect the bottom surface to check for any water penetration.
Inspection:	Contractor and a representative of the membrane manufacturer shall inspect the waterproofing assembly and notify the contractor of any defects. All defects shall be corrected.
Topping/ Overburden:	Nominal 8" x 4" x 2" or 12" x 12" x 2" Hanover Prestbrick or Traditional Concrete Paver, attached with one SikaTile-475 LHT thin set mortar with 1/2" x 1/2" x 1/2" notched trowel.
Maximum Design Pressure:	-502.5 psf (See General Limitation #9)

GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance, refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Required integrity flood testing report shall be provided to the Building Official for review at time of final inspection.
3. All work shall be performed by a Contractor licensed to do roofing/waterproofing and be an applicator trained by Sika Corporation. Sika Corporation shall supply a list of approved applicators to the authority having jurisdiction.
4. Flashings shall be installed according to the manufacturers published standard details, specific details, approved by Sika Corporation and shall be submitted to the Building Official for review.
5. Contractor shall submit to the Building Official for review the system specifications and details. Submission of these documents, as well as the proper application and installation of all materials shall be the sole responsibility of the contractor.
6. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform with Roofing Application Standard RAS 111 and the wind load requirements of applicable Building Code.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. A non-skid surfacing is required for all pedestrian areas, plaza decks or balconies.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 61G20-3 of the Florida Administrative Code.
11. Sikalastic shall not be installed over lightweight insulating concrete.
12. All approved products listed herein shall be labeled in compliance with TAS 121 and shall bear the imprint or identifiable marking of the manufacturer's name or logo and following statement: "Miami-Dade County Product Control Approved" or the Miami-Dade County Product Control Seal as shown below.



END OF THIS ACCEPTANCE



NOA No.: 25-0623.09
Expiration Date: 07/09/31
Approval Date: 07/16/26
Page 33 of 33