



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)
BOARD AND CODE ADMINISTRATION DIVISION

NOTICE OF ACCEPTANCE (NOA)

MIAMI-DADE COUNTY
PRODUCT CONTROL SECTION

11805 SW 26 Street, Room 208
Miami, Florida 33175-2474
T (786)315-2590 F (786) 31525-99

www.miamidade.gov/economy

Seaman Corporation
1000 Venture Boulevard
Wooster, OH 44691

SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

DESCRIPTION: FiberTite Single Ply Roof Systems over Cementitious Wood Fiber Decks.

LABELING: Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

RENEWAL of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

TERMINATION of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

ADVERTISEMENT: The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

INSPECTION: A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA renews NOA #20-0414.12 and consists of pages 1 through 7.
The submitted documentation was reviewed by Alex Tigera.

01/15/26



NOA No.: 25-0722.09
Expiration Date: 01/05/31
Approval Date: 01/15/26
Page 1 of 7

ROOFING SYSTEM APPROVAL

Category:	Roofing
Sub-Category:	Single Ply
Material:	KEE
Deck Type:	Cementitious Wood Fiber
Maximum Design Pressure	-185 psf

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
FiberTite	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite-XT	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite-SM	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite-XTreme	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
Style 80	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
Style 80M	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite FB	54" x 100'	ASTM D 6754	KEE, fleece-backed, single ply membrane
FiberTite-XT FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
FiberTite-SM FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
Style 80 FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
Style 80-M FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
FTR 60-mil Non-Reinforced	0.060" x 54" x 24'	ASTM D 6754	KEE flashing accessory
FTR Cones	1" to 8"	ASTM D 6754	Premolded "KEE" pipe flashing
FTR Corners	2' x 2'	ASTM D 6754	Premolded "KEE" corner flashing (4 per unit)
FiberClad	48" x 120"	N/A	Polymeric coated G-90 galvanized steel or stainless steel
Tuff Trac	5/32" x 36" x 40" 1/4" x 24" x 48"	N/A	Vinyl walk way; Vinyl protection pad
FTR-190e	5 gal. pails	Proprietary	Solvent based bonding adhesive
FTR 490		Proprietary	One side "substrate only" fleece backed water based adhesive
FTR 601	5 gal. pails	Proprietary	Elastomeric, one step foamable adhesive
FTR 601 PG	5 gal. or 50 gal. pails	Proprietary	Two-component, VOC free, polyurethane adhesive

APPROVED INSULATIONS:**TABLE 2**

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
FTR-Value, FTR-Value H, FTR-Value A	Isocyanurate Insulation	Seaman Corporation
ACFoam Composite	Isocyanurate Insulation with perlite facer	Atlas Roofing Corporation
ACFoam-II	Isocyanurate Insulation	Atlas Roofing Corporation
DensDeck Roof Board, DensDeck Prime Roof Board	Silicon treated gypsum	Georgia-Pacific Gypsum LLC
H-Shield	Isocyanurate Insulation	Hunter Panels, a div. of Carlisle Const. Materials, LLC
ENRGY 3	Isocyanurate Insulation	Johns Manville Corporaton
Multi-Max FA-3	Polyisocyanurate foam insulation	Rmax Operating, LLC
Thermarroof Composite-3	Polyisocyanurate/perlite composite insulation.	Rmax Operating, LLC
SECUROCK Gypsum-Fiber Roof Board	Gypsum coverboard	USG Corporation

APPROVED FASTENERS:**TABLE 3**

<u>Fastener Number</u>	<u>Product Name</u>	<u>Product Description</u>	<u>Dimensions</u>	<u>Manufacturer (With Current NOA)</u>
1.	Polymer GypTec	Fastener for cementitious and gypsum decks	Various	OMG, Inc.
2.	Polymer GypTec Insulation Plate	Round Galvalume AZ55 plate	3" round	OMG, Inc
3.	Millennium One Step Foamable Adhesive	A two component, low rise, polyurethane foam adhesive		Adco Products, Inc. dba Royal Adhesives & Sealants
4.	Millennium PG-1 Low Viscosity Insulation Adhesive	A two component, low rise, polyurethane foam adhesive		Adco Products, Inc. dba Royal Adhesives & Sealants
5.	Polyset Commercial Roof Adhesive	Polyurethane adhesive		ICP Adhesives and Sealants, Inc.



EVIDENCE SUBMITTED:

<u>Test Agency/Identifier</u>	<u>Name</u>	<u>Report</u>	<u>Date</u>
Factory Mutual Research Corp.	FM 4470	1Z2A5.AM	01/12/96
	FM 4470	Z3A8.AM	08/13/97
	FM 4470	3002471	10/06/99
	FM 4470	3013068	09/23/03
	FM 4470	3024311	11/01/06
	FM 4470	RR3022147	03/24/08
	FM 4470	RR3022147 Letter	10/07/09
	FM 4470	797-05851-267	09/13/10
	FM 4470	3051607	03/25/15
Underwriters Laboratories	UL790	98NK12510	08/11/98
	UL790	98NK17212	08/21/98
Trinity ERD	TAS 114	4006.08.00-1-R1	10/18/05
	TAS 117 & ASTM D6862	C850SC.11.07-R1	08/07/09
	TAS 114	4006.07.97-1-R1	07/15/10
	TAS 114	4015.10.96-1-R1	07/20/10
	ASTM D 6754	S47410.12.14	12/15/14
	FM 4474 / TAS 114	SMN-SC10155.01.16	01/27/16
Atlantic & Caribbean Roof Consulting, LLC	TAS 114	ACRC 15-030	12/14/15
	TAS 114	ACRC 15-031	12/14/15

APPROVED ASSEMBLIES

Membrane Type:	Single Ply, KEE
Deck Type 5I:	Cementitious Wood Fiber, Insulated
Deck Description:	Cementitious wood fiber
System Type A(1):	One or more layers of insulation adhered with approved adhesive, membrane adhered

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of the following insulations:

<u>Base Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
FTR-Value, ENRGY 3 Minimum: 1.5" thick	N/A	N/A
FTR-Value H, H-Shield (<i>only with Polyset Commercial Roof Adhesive</i>) Minimum: 1.5" thick	N/A	N/A
FTR-Value A, ACFoam-II (<i>not for use with Polyset Commercial Roof Adhesive</i>) Minimum: 1.5" thick	N/A	N/A

Note: All insulation shall be adhered to the substrate in $\frac{3}{4}$ " to 1" wide beads spaced 12" o.c. of FTR 601 or FTR 601 PG or Millennium One Step Foamable Adhesive or Millennium PG-1 Low Viscosity Insulation Adhesive or Polyset Commercial Roof Adhesive. Refer to Roofing Application Standard RAS 117 for insulation attachment. Insulation listed as base layer only shall be used only as base layers with a second layer of approved top layer insulation installed as the final membrane substrate.

Membrane: FiberTite, FiberTite-XT, FiberTite-SM, FiberTite-XTreme, Style 80 or Style 80-M roof cover adhered with FTR-190e Bonding Adhesive applied at a rate of 1 gal/sq. to the back side of the membrane and to the substrate. The outside 1.5" of the lap is heat welded.

Or

FiberTite-FB, FiberTite-XT FB, FiberTite-SM FB, Style 80 FB or Style 80-M FB roof cover adhered with hot asphalt at 25 lbs/sq. or FTR-290 adhesive at 1 gal/sq. or FTR-490 water based adhesive at 100 ft²/gal. The outside 1.5" of the lap is heat welded.

Maximum Design Pressure: -162.5 psf (See General Limitation #9)



Membrane Type: Single Ply, KEE

Deck Type 5I: Cementitious Wood Fiber, Insulated

Deck Description: Cementitious wood fiber

System Type A(2): One or more layers of insulation adhered with approved adhesive, membrane adhered

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of the following insulations:

<u>Base Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
FTR-Value, ENRGY 3 Minimum: 1.5" thick	N/A	N/A
FTR-Value H, H-Shield (<i>only with Polyset Commercial Roof Adhesive</i>) Minimum: 1.5" thick	N/A	N/A
FTR-Value A, ACFoam-II (<i>not for use with Polyset Commercial Roof Adhesive</i>) Minimum: 1.5" thick	N/A	N/A
<u>Top Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
DensDeck Prime Roof Board, SECUROCK Gypsum-Fiber Roof Board Minimum: 1/4" thick	N/A	N/A

Note: All insulation shall be adhered to the substrate in 3/4" to 1" wide beads spaced 12" o.c. of FTR 601 or FTR 601 PG or Millennium One Step Foamable Adhesive or Millennium PG-1 Low Viscosity Insulation Adhesive or Polyset Commercial Roof Adhesive. Refer to Roofing Application Standard RAS 117 for insulation attachment. Insulation listed as base layer only shall be used only as base layers with a second layer of approved top layer insulation installed as the final membrane substrate.

Membrane: FiberTite, FiberTite-XT, FiberTite-SM, FiberTite-XTreme, Style 80 or Style 80-M roof cover adhered with FTR-190e Bonding Adhesive applied at a rate of 1 gal/sq. to the back side of the membrane and to the substrate. The outside 1.5" of the lap is heat welded.

Or

FiberTite-FB, FiberTite-XT FB, FiberTite-SM FB, Style 80 FB or Style 80-M FB roof cover adhered with hot asphalt at 25 lbs/sq. or FTR-290 adhesive at 1 gal/sq. or FTR-490 water based adhesive at 100 ft²/gal. or spatter-applied with Polyset Commercial Roof Adhesive. The outside 1.5" of the lap is heat welded.

Maximum Design Pressure: -185 psf (See General Limitation #9)



GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance, refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each sidelap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq. **Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**
5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117 and/or RAS 137. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform with Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 61G20-3 of the Florida Administrative Code.

END OF THIS ACCEPTANCE

